

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 May 2003 (22.05.2003)

PCT

(10) International Publication Number
WO 03/041757 A2

(51) International Patent Classification⁷: A61L 29/00

94022 (US). WRIGHT, Jeremy, Corwin; 631 Cuesta Drive, Los Altos, CA 94024-4135 (US).

(21) International Application Number: PCT/US02/36716

(22) International Filing Date:
14 November 2002 (14.11.2002)

(74) Agents: DATE, Vandana et al.; ALZA CORPORATION, 1900 Charleston Road, P.O. Box 7210, Mountain View, CA 94039-7210 (US).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
(40336)307 14 November 2001 (14.11.2001) US
(40399)882 31 July 2002 (31.07.2002) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.


(71) Applicant: ALZA CORPORATION [US/US]; 1900 Charleston Road, P.O. BOX 7210, Mountain View, CA 94039-7210 (US).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors: CHEN, Guohua; 399 Sunset Avenue, Sunnyvale, CA 94086 (US). HOUSTON, Paul, Ricky; 3889 Blackstone Court, Hayward, CA 94542 (US). KLEINER, Lothar, Walther; 295 Los Altos Court, Los Altos, CA

[Continued on next page]

(54) Title: CATHETER INJECTABLE DEPOT COMPOSITIONS AND USES THEREOF



(57) Abstract: Catheter injectable depot compositions are provided that include a bioerodible, biocompatible polymer, a solvent having miscibility in water of less than or equal to 7 wt.% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, a thixotropic agent, and a beneficial agent. The solvent comprises an aromatic alcohol, an ester of an aromatic acid, an aromatic ketone, or mixtures thereof. The compositions have substantially improved the shear thinning behavior and reduced injection force, rendering the compositions readily implanted beneath a patient's body surface by injection.

WO 03/041757 A2



Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

CATHETER INJECTABLE DEPOT COMPOSITIONS AND USES THEREOF**CROSS-REFERENCE TO RELATED APPLICATION**

[0001] This application claims the benefit of U.S. Provisional Application
5 Nos. 60/336,307, filed on November 14, 2001 and 60/399,882 filed on July 31,
2002.

BACKGROUND OF THE INVENTION**Field of the Invention**

10 **[0002]** The present invention relates to a depot composition that can be
injected into a desired location within a patient's body to form an implant,
which provides for sustained release of a beneficial agent. More particularly,
the present invention pertains to depot compositions that exhibit improved
shear thinning behavior and a low injection force. The present invention also
15 relates to a method of using the depot composition to administer a beneficial
agent to a patient.

Description of the Related Art

[0003] Biodegradable polymers have been used for many years in
20 medical applications. Illustrative devices composed of the biodegradable
polymers include sutures, surgical clips, staples, implants, and drug delivery
systems. The majority of these biodegradable polymers have been based
upon glycolide, lactide, caprolactone, and copolymers thereof.

25 **[0004]** The biodegradable polymers can be thermoplastic materials,
meaning that they can be heated and formed into various shapes such as
fibers, clips, staples, pins, films, etc. Alternatively, they can be thermosetting
materials formed by crosslinking reactions, which lead to high-molecular-
weight materials that do not melt or form flowable liquids at high temperatures.
30 Although thermoplastic and thermosetting biodegradable polymers have many
useful biomedical applications, there are several important limitations to their
use in the bodies of various animals including humans, animals, birds, fish,
and reptiles.

[0005] Solid implant drug delivery systems containing a drug incorporated in thermoplastic or thermosetting biodegradable polymers have been widely used successfully. Such implants have to be inserted into the body through an incision which is sometimes larger than desired by the medical profession and occasionally lead to a reluctance of the patients to accept such an implant or drug delivery system. The following patents U.S. Patent Nos. 5,456,679; 5,336,057; 5,308,348; 5,279,608; 5,234,693; 5,234,692; 5,209,746; 5,151,093; 5,137,727; 5,112,614; 5,085,866; 5,059,423; 5,057,318; 4,865,845; 4,008,719; 3,987,790 and 3,797,492 are believed to be representative of such drug delivery systems and are incorporated herein by reference. These patents disclose reservoir devices, osmotic delivery devices and pulsatile delivery devices for delivering beneficial agents.

[0006] Injecting drug delivery systems as small particles, microspheres, or microcapsules avoids the incision needed to implant drug delivery systems. However, these materials do not always satisfy the demand for a biodegradable implant. These materials are particulate in nature, do not form a continuous film or solid implant with the structural integrity needed for certain prostheses, the particles tend to aggregate and thus their behavior is hard to predict. When inserted into certain body cavities such as a mouth, a periodontal pocket, the eye, or the vagina where there is considerable fluid flow, these small particles, microspheres, or microcapsules are poorly retained because of their small size and discontinuous nature. Further, if there are complications, removal of microcapsule or small-particle systems from the body without extensive surgical intervention is considerably more difficult than with solid implants. Additionally, manufacture, storage and injectability of microspheres or microcapsules prepared from these polymers and containing drugs for release into the body present problems.

30

[0007] The art has developed various drug delivery systems in response to the aforementioned challenges. The following patents U.S. Patent Nos. 5,990,194; 5,780,044; 5,733,950; 5,620,700; 5,599,552; 5,556,905 5,278,201;

5,242,910 and 4,938,763; and PCT publication WO 98/27962 are believed to be representative and are incorporated herein by reference. These patents disclose polymer compositions for injectable implants using solvents and/or plasticizers.

5

[0008] Previously described polymer compositions for injectable implants have used solvent/plasticizers that are very or relatively soluble in aqueous body fluids to promote rapid solidification of the polymer at the implant site and promote diffusion of drug from the implant. Rapid migration of water into such polymeric implants utilizing water soluble polymer solvents when the implants are placed in the body and exposed to aqueous body fluids presents a serious problem. The rapid water uptake often results in implants having pore structures that are non-homogeneous in size and shape. Typically, the surface pores take on a finger-like pore structure extending for as much as one-third of a millimeter or more from the implant surface into the implant, and such finger-like pores are open at the surface of the implant to the environment of use. The internal pores tend to be smaller and less accessible to the fluids present in the environment of use. The rapid water uptake characteristic often results in uncontrolled release of beneficial agent that is manifested by an initial, rapid release of beneficial agent from the polymer composition, corresponding to a "burst" of beneficial agent being released from the implant. The burst often results in a substantial portion of the beneficial agent, if not all, being released in a very short time, e.g., hours or 1-2 days. Such an effect can be unacceptable, particularly in those circumstances where a controlled delivery is desired, i.e., delivery of beneficial agent in a controlled manner over a period of greater than two weeks or up to a month, or where there is a narrow therapeutic window and release of excess beneficial agent can result in adverse consequences to the subject being treated, or where it is necessary to mimic the naturally-occurring daily profile of beneficial agents, such as hormones and the like, in the body of the subject being treated.

[0009] Accordingly, when such devices are implanted, the finger-like pores allow very rapid uptake of aqueous body fluids into the interior of the implant with consequent immediate and rapid dissolution of significant quantities of beneficial agent and unimpeded diffusion of beneficial agent into
5 the environment of use, producing the burst effect discussed above.

[0010] Furthermore, rapid water uptake can result in premature polymer precipitation such that a hardened implant or one with a hardened skin is produced. The inner pores and much of the interior of the polymer containing
10 beneficial agent are shut off from contact with the body fluids and a significant reduction in the release of beneficial agent can result over a not insignificant period of time ("lag time"). That lag time is undesirable from the standpoint of presenting a controlled, sustained release of beneficial agent to the subject being treated. What one observes, then, is a burst of beneficial agent being
15 released in a short time period immediately after implantation, a lag time in which no or very little beneficial agent is being released, and subsequently continued delivery of beneficial agent (assuming beneficial agent remains after the burst) until the supply of beneficial agent is exhausted.

[0011] Various approaches to control burst and modulate and stabilize the delivery of the beneficial agent have been described. The following patents U.S. Patent Nos. 6,130,200; 5,990,194; 5,780,044; 5,733,950; 5,656,297; 5,654,010; 4,985,404 and 4,853,218 and PCT publication WO
20 98/27962 are believed to be representative and are incorporated herein by reference. Notwithstanding some success, those methods have not been
25 entirely satisfactory for the large number of beneficial agents that would be effectively delivered by implants.

[0012] An additional problem encountered with prior solvent-based
30 depot compositions is that the viscosity of the injectable composition is relatively high, particularly when higher molecular weight polymers are used, and the injection force needed to introduce the composition into a patient's body is therefore high as well (see, e.g. U.S. Patent No. 6,130,200). However,

the high viscosity of the gel is desirable to maintain the integrity of the depot after injection and during the dispensing period and also facilitate desired suspension characteristics of the beneficial agent in the gel.

5 [00013] To address this problem, those working in the field have employed various methods to reduce overall viscosity of the composition, such as the use of lower molecular weight polymers, a lower polymer to solvent ratio, and agents that provide viscosity reduction. See, for example, U.S. Patent No. 5,733,950; 5,780,044, and 5,990,194 to Dunn et al. International
10 application WO 98/27962. These patents and publications describe the formation of a thixotropic gel composition that provides for shear thinning and more acceptable injectability of the gel, such that lower injection forces are needed to expel the gel from a syringe and also lower the likelihood of substantial discomfort to a subject by use of smaller needles than would
15 otherwise be required.

[00014] Notwithstanding some success, the previously described systems have not been entirely satisfactory. For example, these approaches can result in drug particle settling; a higher initial release burst; relatively large
20 amounts of emulsifying agent, e.g., about one-third of the total weight of the composition; manufacturing problems related to solvent volatility; denaturation of proteins and peptide drugs, and the like. Additionally, the requirement that the bioerodible polymer have a low molecular weight is quite restrictive from a manufacturing standpoint.

25 [00015] It has been discovered that in certain systems biodegradable polymers dissolved in a suitable polymer solvent, and in certain embodiments mixed with a thixotropic agent, result in depot compositions exhibiting substantially significantly improved shear thinning and further reduced injection
30 force as compared to previously described depot gel formulations. These depot compositions have modified flow characteristics without the formation of an emulsion but still result in thixotropic compositions that are readily injectable through needles and/or catheters having a gauge that when used is

not unduly uncomfortable to a subject. Also, use of such smaller amounts of an agent that imparts thixotropic properties to the gel may allow for smaller depot volume and mass without diminishing delivery of a required amount of beneficial agent over a prolonged period of time for an intended therapeutic effect.

SUMMARY OF THE INVENTION

[00016] The present invention is directed to the aforementioned needs in the art, and provides a catheter injectable depot composition that exhibits improved shear thinning behavior and thereby enables further reduced injection force and use of a small diameter (e.g., 16 gauge and higher) needle and/or catheter. In particular, the catheter injectable depot composition increases the shear thinning behavior and composition homogeneity, without resulting in settling of the beneficial agent. Additionally, the catheter injectable depot composition reduces the injection force while maintaining high viscosity of the composition at low shear, thus maintaining the intactness of the composition. The composition provides sustained release of a beneficial agent while limiting any initial burst effect, and offers increased formulation flexibility with regard to the polymer/solvent ratio and the molecular weight of the bioerodible polymer.

20

[00017] In one aspect, then, the invention is directed to a catheter injectable depot composition comprising:

- (a) a bioerodible, biocompatible polymer;
- (b) a solvent having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein said solvent is an aromatic alcohol;
- (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- (d) a beneficial agent.

[00018] In another aspect, the invention is directed to a catheter injectable depot composition comprising:


- (a) a bioerodible, biocompatible polymer;
- (b) an aromatic alcohol having miscibility in water of less than 5 or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



- (c) in which Ar is a substituted or unsubstituted aryl or 10 heteroaryl group, n is zero or 1, and L is a linking moiety;
- (d) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of 15 the solvent and the thixotropic agent; and
- (e) a beneficial agent.

[00019] In another aspect, the invention is directed to a catheter injectable depot composition comprising:

- (a) approximately 5 wt.% to approximately 90 wt.% of a 20 biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000, preferably approximately 5,000 to approximately 50,000, more preferably approximately 8,000 to approximately 30,000;
- (b) an aromatic alcohol having miscibility in water of less than 25 or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



- (c) in which Ar is a substituted or unsubstituted aryl or 30 heteroaryl group, n is zero or 1, and L is a linking moiety;
- (d) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols

and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and

(e) a beneficial agent.

5 [00020] In another aspect, the invention is directed to a catheter injectable depot composition comprising:

(a) a bioerodible, biocompatible polymer;

(b) a solvent selected from the group consisting of aromatic alcohols, esters of aromatic acids, aromatic ketones, and mixtures thereof,
10 said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith;

(c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols
15 and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and

(d) a beneficial agent.

20 [00021] In another aspect, the invention is directed to an catheter injectable depot composition comprising:

(a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to
25 approximately 120,000, preferably approximately 5,000 to approximately 50,000, more preferably approximately 8,000 to approximately 30,000;

(b) a solvent selected from the group consisting of an aromatic alcohol, an ester of an aromatic acid, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and
30 present in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I) wherein Ar, n and L are as defined above;

- (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- (d) a beneficial agent.

[00022] The lower alkanols are straight or branched chain alcohols having 2-6 carbon atoms as exemplified by ethanol, propanol, isopropanol and the like. A preferred thixotropic agent is ethanol. The composition may include an amount of ethanol that is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the thixotropic agent. The composition may include an amount of ethanol that is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the thixotropic agent. The composition may include an amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the thixotropic agent.

- [00023]** In another aspect, the invention is directed to a catheter injectable depot composition comprising:
- (a) a bioerodible, biocompatible polymer;
- (b) an aromatic alcohol having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith; and
- (c) a beneficial agent,
- (d) wherein the composition is free of monohydric lower alkanols.

- [00024]** In another aspect, the invention is directed to a catheter injectable depot composition comprising:
- (a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight

average molecular weight in the range of approximately 1,000 to approximately 120,000, preferably approximately 5,000 to approximately 50,000, more preferably approximately 8,000 to approximately 30,000;

- (b) an aromatic alcohol having miscibility in water of less than or equal to 5% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



- (c) in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety; and
- (d) a beneficial agent,
- (e) wherein the composition is free of monohydric lower alkanols.

15

[00025] In another aspect, the invention is directed to a catheter injectable depot composition comprising:

- (a) a bioerodible, biocompatible polymer;
- (b) a solvent selected from the group consisting of esters of aromatic acids, aromatic ketones, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith;
- (c) an effective thixotropic amount of an aromatic alcohol having miscibility in water of less than or equal to 7%; and
- (d) a beneficial agent,
- (e) wherein the composition is free of monohydric lower alkanols.

25

[00026] In another aspect, the invention is directed to a catheter injectable depot composition comprising:

- (a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to

approximately 120,000, preferably approximately 5,000 to approximately 50,000, more preferably approximately 8,000 to approximately 30,000;

(b) an ester of an aromatic acid, said ester having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith;

(c) an effective thixotropic amount of an aromatic alcohol having miscibility in water of less than or equal to 7%, wherein the aromatic alcohol has the structural formula (I) wherein Ar, n and L are as defined above; and

(d) a beneficial agent,

(e) wherein the composition is free of monohydric lower alkanols.

[00027] In another aspect, the invention comprises a method of administering, locally or systemically, a beneficial agent to a subject which comprises implanting beneath the subject's body surface a catheter injectable composition as described above. Preferably, the system releases 40% or less by weight of the beneficial agent present in the viscous gel within the first 24 hours after implantation in the subject. More preferably, 30% or less by weight of the beneficial agent will be released within the first 24 hours after implantation, and the implanted composition has a burst index of 12 or less, preferably 8 or less.

[00028] In another aspect, the invention comprises a method of administering, locally or systemically, a beneficial agent to a subject comprising the steps of:

(1) providing a catheter having a catheter injectable depot composition as described above;

(2) delivering the depot composition to the subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

[00029] In another aspect, the invention pertains to a catheter injectable depot composition and a method of administering such composition as described above, wherein the viscous gel further comprises a polymer selected from the group consisting of polylactides, polyglycolides, poly(caprolactone), polyanhydrides, polyamines, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyphosphoesters, polyorthocarbonates, polyphosphazenes, succinates, poly(malic acid), poly(amino acids), polyvinylpyrrolidone, polyethylene glycol, polyhydroxycellulose, polyphosphoesters, polysaccharides, chitin, chitosan, hyaluronic acid, and copolymers, terpolymers and mixtures thereof. In preferred embodiments, the polymer is a lactic acid based polymer. Preferably, the polylactic acid polymer may have a weight average molecular weight in the range of about 1,000 to about 120,000; preferably about 5,000 to about 50,000; and more preferably about 8,000 to about 30,000.

15

[00030] In preferred embodiments, the solvent is selected from the aromatic alcohol, lower alkyl and aralkyl esters of aryl acids; aryl, aralkyl and lower alkyl ketones; and lower alkyl esters of citric acid. Preferably, the solvent is selected from benzyl alcohol, benzyl benzoate and ethyl benzoate.

[00031] In preferred embodiments, the composition is free of solvents having miscibility in water that is greater than 7 wt.% at 25°C. Preferably the solvent has miscibility in water of less than 7 wt.%, more preferably less than 5 wt%, and more preferably less than 3 wt%.

25

[00031] In another aspect, the invention pertains to a catheter injectable depot composition and a method of administering such composition as described above, wherein the beneficial agent is selected from a drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-inflammatory agents, antiproliferative agents, antimitotic agents, angiogenic agents, anticoagulants, fibrinolytic agents, growth factors, antibodies, ocular drugs, and metabolites, analogs, derivatives,

30

fragments, and purified, isolated, recombinant and chemically synthesized versions of these species. In preferred embodiments, the beneficial agent is human growth hormone, methionine-human growth hormone; des-phenylalanine human growth hormone, alpha-, beta- or gamma-interferon, erythropoietin, glugacon, calcitonin, heparin, interleukin-1, interleukin-2, Factor VIII, Factor IX, luteinizing hormone, relaxin, follicle-stimulating hormone, atrial natriuretic factor, filgrastim epidermal growth factors (EGFs), platelet-derived growth factor (PDGFs), insulin-like growth factors (IGFs), fibroblast-growth factors (FGFs), transforming-growth factors (TGFs), interleukins (ILs), colony-stimulating factors (CSFs, MCFs, GCSFs, GMCSFs), Interferons (IFNs), endothelial growth factors (VEGF, EGFs), erythropoietins (EPOs), angiopoietins (ANGs), placenta-derived growth factors (PIGFs), and hypoxia induced transcriptional regulators (HIFs). Preferably, the beneficial agent is present in an amount of from 0.1 to 50% by weight of the combined amounts of the polymer, the solvent and the beneficial agent. In preferred embodiments, the beneficial agent is in the form of particles dispersed or dissolved in the viscous gel, wherein the beneficial agent is in the form of particles having an average particle size of from 0.1 to 250 microns. In certain preferred embodiments, the beneficial agent is in the form of particles wherein the particle further comprises a component selected from the group consisting of a stabilizing agent, bulking agent, chelating agent and a buffering agent.

BRIEF DESCRIPTION OF THE DRAWINGS

[00032] The foregoing and other objects, features and advantages of the present invention will be more readily understood upon reading the following detailed description in conjunction with the drawings in which:

[00033] Figure 1 is a graph illustrating the rheological behavior of depot vehicles formulated with different solvents, i.e., Formulations 5, 6 and 7.

[00034] Figure 2 is a graph illustrating the injection force required to dispense the Formulations 5, 6 and 7 from a 24-gauge needle at 1 ml/minute, at room temperature.

[00035] Figure 3 is a graph illustrating the injection force required to dispense catheter injectable depot compositions formulated with varying poly(lactide-co-glycolide) weight average molecular weights in combination with benzyl benzoate or benzyl alcohol from a 24 gauge needle at 1 ml/minute, at room temperature.

[00036] Figure 4 is a graph illustrating the injection force required to dispense depot compositions formulated with varying poly(lactide-co-glycolide) weight average molecular weights in combination with benzyl benzoate or benzyl alcohol or mixtures thereof from a 24 gauge needle at 1 ml/minute, at room temperature.

[00037] Figure 5 is a graph illustrating the rheological behavior of depot vehicles formulated with different solvents, i.e., Formulations 8, 9 and 10.

[00038] Figure 6 is a graph illustrating the injection force required to dispense various depot compositions, i.e. Formulations 8, 9 and 10 from a 24 gauge needle at 1 ml/minute, at room temperature.

[00039] Figure 7 is a graph illustrating the rheological behavior of depot vehicles formulated with different solvents, i.e., Formulations 11, 12 and 13.

[00040] Figure 8 is a graph illustrating the rheological behavior of depot vehicles formulated with different solvents, i.e., Formulations 11, 14 and 15.

[00041] Figure 9 is a graph illustrating the injection force required to dispense various depot compositions, i.e. Formulations 11, 12 and 13 from a 24 gauge needle at 1 ml/minute, at room temperature.

[00042] Figure 10 is a graph illustrating the injection force required to dispense various depot compositions, i.e. Formulations 11, 14 and 15 from a 24 gauge needle at 1 ml/minute, at room temperature.

[00043] Figure 11 is a graph illustrating the *in vivo* release profile of human growth hormone ("hGH") obtained from various depot compositions, including those of the present invention (Formulations 16-18).

5

[00044] Figure 12 is a graph illustrating the *in vivo* release profile of human growth hormone ("hGH") obtained from various depot compositions (Formulations 18 and 19).

10 [00045] Figure 13 is a graph illustrating the *in vivo* release profile of bupivacaine obtained from various depot compositions, including those of the present invention (Formulations 20 and 21).

[00046] Figure 14 is a graph illustrating the *in vivo* release profile of
15 bupivacaine obtained from various depot compositions, including those of the present invention (Formulations 22 and 21).

[00047] Figure 15 is a graph illustrating the *in vivo* release profile of
20 bupivacaine obtained from depot compositions, including those of the present invention (Formulations 23 and 24).

[00048] Figure 16 illustrates the stability of hGH in the various depot
formulations, including those of the present invention, as a function of time at 5
°C.

25

[00049] Figure 17 illustrates the injection force of various depot
formulations, including those of the present invention, as a function of the
loading levels and the particle sizes of beneficial agent.

30 [00050] Figure 18 illustrates the stability of PDGF in the various depot
formulations, including those of the present invention, as a function of time at 5
°C.

[00051] Figure 19 illustrates the stability of PDGF in the various depot formulations, including those of the present invention, as a function of time at 25 °C.

5 [00052] Figure 20 illustrates the stability of PDGF in the various depot formulations, including those of the present invention, as a function of time at 40 °C.

[00053] Figure 21 is a graph illustrating the *in vitro* release of PDGF
10 obtained from various depot compositions, including those of the present invention (Formulations 43 - 46).

[00054] Figure 22 illustrates the injection force as a function of catheter lengths, of the depot formulation of the present invention (formulation 40).

15

DETAILED DESCRIPTION OF THE INVENTION

Overview and Definitions:

[00055] The present invention is directed to a catheter injectable depot composition that serves as an implanted sustained release beneficial agent
20 delivery system after injection into a patient's body. In particular, the present invention pertains to a catheter injectable depot composition that exhibits improved shear thinning behavior and a low injection force. By maintaining high viscosity of the composition at low shear, the intactness of the composition is maintained. The present invention also relates to a method of using the
25 catheter injectable depot composition to administer a beneficial agent to a patient. The catheter injectable depot composition is a gel formed from a bioerodible, biocompatible polymer, a solvent having miscibility in water of less than or equal to 7% at 25°C, preferably less than or equal to 5% at 25°C, the solvent being selected from a group consisting of an aromatic alcohol, an
30 aromatic acid ester, and an aromatic ketone; and a beneficial agent. In certain embodiments, the catheter injectable depot composition further comprises a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being

selected from the group consisting essentially of lower alkanols, the amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent.

- 5 [00056] The composition provides sustained release of the beneficial agent by restricting water migration from the aqueous environment surrounding the implant system, thus delivering the beneficial agent over a prolonged period of time. Water uptake is controlled by virtue of the water-immiscible aromatic alcohol. Because the polymer of the composition is
10 bioerodible, the implant system does not have to be surgically removed after beneficial agent is depleted from the implant.

- [00057] Generally, the compositions of the invention are gel-like and form with a substantially homogeneous non-porous structure throughout the implant
15 upon implantation and during drug delivery, even as it hardens. Furthermore, while the polymer gel implant will slowly harden when subjected to an aqueous environment, the hardened implant may maintain a rubbery (non-rigid) composition with the glass transition temperature T_g being below 37°C.

- 20 [00058] Because the aromatic alcohol in these compositions itself acts as a thixotropic agent and thus substantially increases shear thinning as well as composition homogeneity, it is not normally necessary to introduce additional thixotropic agents. In some embodiments, however, shear thinning and/or homogeneity may be further improved (thereby improving release
25 characteristics) by incorporating additional thixotropic agents. In this regard, although the aromatic alcohol in these compositions itself acts as a thixotropic agent, it has been discovered that addition of a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition as described herein, provides a catheter injectable depot
30 composition having surprisingly substantially significantly improved shear thinning behavior and further reduced injection force as compared to previously described depot compositions. In some embodiments, pore formers and solubility modulators of the beneficial agent may be added to the

implant systems to provide desired release profiles from the implant systems, along with typical pharmaceutical excipients and other additives that do not change the beneficial aspects of the present invention.

- 5 [00059] The preferred compositions herein allow beneficial agent to be loaded into the interior of the polymer at levels that are above that required to saturate the beneficial agent in water, thereby facilitating zero order release of beneficial agent. Additionally, the preferred compositions may provide viscous gels that have a glass transition temperature that is less than 37°C, such that
10 the gel remains non-rigid for a period of time after implantation of 24 hours or more.

[00060] In describing and claiming the present invention, the following terminology will be used in accordance with the definitions set out below.

15

- [00061] The singular forms "a," "an" and "the" include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to "a solvent" includes a single solvent as well as a mixture of two or more different solvents, reference to "a beneficial agent" includes a single beneficial
20 agent as well as two or more different beneficial agents in combination, reference to "an aromatic alcohol" includes a single aromatic alcohol as well as a mixture of two or more different aromatic alcohols, and the like.

- [00062] The term "beneficial agent" means an agent that affects a
25 desired beneficial, often pharmacological, effect upon administration to a human or an animal, whether alone or in combination with other pharmaceutical excipients or inert ingredients.

- [00063] As used herein, the term "polynucleotide" refers to a polymeric
30 form of nucleotides of any length, either ribonucleotides or deoxyribonucleotides, and includes double- and single-stranded DNA and RNA. It also includes known types of modifications, substitutions, and internucleotide modifications, which are known in the art.

[00064] As used herein, the term "recombinant polynucleotide" refers to a polynucleotide of genomic, cDNA, semisynthetic, or synthetic origin which, by virtue of its origin or manipulation: is not associated with all or a portion of a polynucleotide with which it is associated in nature; is linked to a
5 polynucleotide other than that to which it is linked in nature; or does not occur in nature.

[00065] As used herein, the term "polypeptide" refers to a polymer of amino acids, including for example, peptides, oligopeptides, and proteins and
10 derivatives, analogs and fragments thereof, as well as other modifications known in the art, both naturally occurring and non-naturally occurring.

[00066] As used herein, the term "purified" and "isolated" when referring to a polypeptide or nucleotide sequence means that the indicated molecule is
15 present in the substantial absence of other biological macromolecules of the same type. The term "purified" as used herein preferably means at least 75% by weight, more preferably at least 85% by weight, more preferably still at least 95% by weight, and most preferably at least 98% by weight, of biological macromolecules of the same type present.

20 [00067] The term "AUC" means the area under the curve obtained from an *in vivo* assay in a subject by plotting blood plasma concentration of the beneficial agent in the subject against time, as measured from the time of implantation of the composition, to a time "t" after implantation. The time t will
25 correspond to the delivery period of beneficial agent to a subject.

[00068] The term "burst index" means, with respect to a particular composition intended for systemic delivery of a beneficial agent, the quotient formed by dividing (i) the AUC calculated for the first time period after
30 implantation of the composition into a subject divided by the number of hours in the first time period (t_1), by (ii) the AUC calculated for the time period of delivery of beneficial agent, divided by the number of hours in the total duration of the delivery period (t_2). For example the burst index at 24 hours is

the quotient formed by dividing (i) the AUC calculated for the first twenty-four hours after implantation of the composition into a subject divided by the number 24, by (ii) the AUC calculated for the time period of delivery of beneficial agent, divided by the number of hours in the total duration of the delivery period.

5 [00069] The phrase "dissolved or dispersed" is intended to encompass all means of establishing a presence of beneficial agent in the gel composition and includes dissolution, dispersion, suspension and the like.

10

[00070] The term "systemic" means, with respect to delivery or administration of a beneficial agent to a subject, that the beneficial agent is detectable at a biologically-significant level in the blood plasma of the subject.

15 [00071] The term "local" means, with respect to delivery or administration of a beneficial agent to a subject, that the beneficial agent is delivered to a localized site in the subject but is not detectable at a biologically significant level in the blood plasma of the subject.

20 [00072] The term "gel vehicle" means the composition formed by mixture of the polymer and solvent in the absence of the beneficial agent.

[00073] The term "prolonged period" means a period of time over which release of a beneficial agent from the implant of the invention occurs, which
25 will generally be about one week or longer, and preferably about 30 days or longer.

[00074] The term "initial burst" means, with respect to a particular composition of this invention, the quotient obtained by dividing (i) the amount
30 by weight of beneficial agent released from the composition in a predetermined initial period of time after implantation, by (ii) the total amount of beneficial agent that is to be delivered from an implanted composition. It is understood that the initial burst may vary depending on the shape and surface

area of the implant. Accordingly, the percentages and burst indices associated with initial burst described herein are intended to apply to compositions tested in a form resulting from dispensing of the composition from a standard syringe.

5

[00075] The term "solubility modulator" means, with respect to the beneficial agent, an agent that will alter the solubility of the beneficial agent, with reference to polymer solvent or water, from the solubility of beneficial agent in the absence of the modulator. The modulator may enhance or retard the solubility of the beneficial agent in the solvent or water. However, in the case of beneficial agents that are highly water soluble, the solubility modulator will generally be an agent that will retard the solubility of the beneficial agent in water. The effects of solubility modulators of the beneficial agent may result from interaction of the solubility modulator with the solvent, or with the beneficial agent itself, such as by the formation of complexes, or with both. For the purposes hereof, when the solubility modulator is "associated" with the beneficial agent, all such interactions or formations as may occur are intended. Solubility modulators may be mixed with the beneficial agent prior to its combination with the viscous gel or may be added to the viscous gel prior to the addition of the beneficial agent, as appropriate.

10
15
20

[00076] The terms "subject" and "patient" mean, with respect to the administration of a composition of the invention, an animal or a human being.

25 [00077] Since all solvents, at least on a molecular level, will be soluble in water (i.e., miscible with water) to some very limited extent, the term "immiscible" as used herein means that 7% or less by weight, preferably 5% or less, of the solvent is soluble in or miscible with water. For the purposes of this disclosure, solubility values of solvent in water are considered to be determined at 25°C. Since it is generally recognized that solubility values as reported may not always be conducted at the same conditions, solubility limits recited herein as percent by weight miscible or soluble with water as part of a range or upper limit may not be absolute. For example, if the upper limit on

30

solvent solubility in water is recited herein as "7% by weight," and no further limitations on the solvent are provided, the solvent "triacetin," which has a reported solubility in water of 7.17 grams in 100 ml of water, is considered to be included within the limit of 7%. A solubility limit in water of less than 7% by weight as used herein does not include the solvent triacetin or solvents having solubilities in water equal to or greater than triacetin.

[00078] The term "bioerodible" refers to a material that gradually decomposes, dissolves, hydrolyzes and/or erodes in situ. Generally, the "bioerodible" polymers herein are polymers that are hydrolyzable, and bioerode in situ primarily through hydrolysis.

[00079] The term "thixotropic" is used in its conventional sense to refer to a gel composition that can liquefy or at least exhibit a decrease in apparent viscosity upon application of mechanical force such as shear force. The extent of the reduction is in part a function of the shear rate of the gel when subjected to the shearing force. When the shearing force is removed, the viscosity of the thixotropic gel returns to a viscosity at or near that which it displayed prior to being subjected to the shearing force. Accordingly, a thixotropic gel may be subjected to a shearing force when injected from a syringe which temporarily reduces its viscosity during the injection process. When the injection process is completed, the shearing force is removed and the gel returns very near to its previous state.

[00080] A "thixotropic agent" as used herein is one that increases the thixotropy of the composition in which it is contained, promoting shear thinning and enabling use of reduced injection force.

[00081] The polymer, solvent and other agents of the invention must be "biocompatible"; that is they must not cause irritation, inflammation or necrosis in the environment of use. The environment of use is a fluid environment and may comprise a subcutaneous, intramuscular, intravascular (high/low flow),

intramyocardial, adventitial, intratumoral, or intracerebral portion, wound sites, tight joint spaces or body cavity of a human or animal.

[00082] The following definitions apply to the molecular structures described herein:

- 5 As used herein, the phrase "having the formula" or "having the structure" is not intended to be limiting and is used in the same way that the term "comprising" is commonly used.

- [00083]** The term "alkyl" as used herein refers to a saturated hydrocarbon group typically although not necessarily containing 1 to about 30 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, t-butyl, octyl, decyl, and the like, as well as cycloalkyl groups such as cyclopentyl, cyclohexyl and the like. Generally, although again not necessarily, alkyl groups herein contain 1 to about 12 carbon atoms. The term "lower alkyl" intends an alkyl group of 1 to 6 carbon atoms, preferably 1 to 4 carbon atoms. "Substituted alkyl" refers to alkyl substituted with one or more substituent groups, and the terms "heteroatom-containing alkyl" and "heteroalkyl" refer to alkyl in which at least one carbon atom is replaced with a heteroatom. If not otherwise indicated, the terms "alkyl" and "lower alkyl" include linear, branched, cyclic, unsubstituted, substituted, and/or heteroatom-containing alkyl or lower alkyl.
- 10
15
20

- [00084]** The term "aryl" as used herein, and unless otherwise specified, refers to an aromatic substituent containing a single aromatic ring or multiple aromatic rings that are fused together, linked covalently, or linked to a common group such as a methylene or ethylene moiety. Preferred aryl groups contain one aromatic ring or two fused or linked aromatic rings, e.g., phenyl, naphthyl, biphenyl, diphenylether, diphenylamine, benzophenone, and the like, and most preferred aryl groups are monocyclic. "Substituted aryl" refers to an aryl moiety substituted with one or more substituent groups, and the terms "heteroatom-containing aryl" and "heteroaryl" refer to aryl in which at least one carbon atom is replaced with a heteroatom. Unless otherwise indicated, the
- 25
30

term "aryl" includes heteroaryl, substituted aryl, and substituted heteroaryl groups.

[00085] The term "aralkyl" refers to an alkyl group substituted with an aryl group, wherein alkyl and aryl are as defined above. The term "heteroaralkyl" refers to an alkyl group substituted with a heteroaryl group. Unless otherwise indicated, the term "aralkyl" includes heteroaralkyl and substituted aralkyl groups as well as unsubstituted aralkyl groups. Generally, the term "aralkyl" herein refers to an aryl-substituted lower alkyl group, preferably a phenyl substituted lower alkyl group such as benzyl, phenethyl, 1-phenylpropyl, 2-phenylpropyl, and the like.

[00086] The term "heteroatom-containing" as in a "heteroatom-containing hydrocarbyl group" refers to a molecule or molecular fragment in which one or more carbon atoms is replaced with an atom other than carbon, e.g., nitrogen, oxygen, sulfur, phosphorus or silicon. Similarly, the term "heterocyclic" refers to a cyclic substituent that is heteroatom-containing, the term "heteroaryl" refers to an aryl substituent that is heteroatom-containing, and the like.

[00087] By "substituted" as in "substituted alkyl," "substituted aryl" and the like, as alluded to in some of the aforementioned definitions, is meant that in the alkyl or aryl moiety, respectively, at least one hydrogen atom bound to a carbon atom is replaced with one or more non-interfering substituents such as hydroxyl, alkoxy, thio, amino, halo, and the like.

25

I. Catheter Injectable Depot Compositions:

[00088] As described previously, catheter injectable depot compositions for delivery of beneficial agents over a prolonged period of time may be formed as viscous gels prior to injection of the depot into a subject. The viscous gel supports dispersed beneficial agent to provide appropriate delivery profiles, which include those having low initial burst, of the beneficial agent as the beneficial agent is released from the depot over time.

[00089] The polymer, solvent and other agents of the invention must be biocompatible; that is they must not cause irritation or necrosis in the environment of use. The environment of use is a fluid environment and may comprise a subcutaneous, intramuscular, intravascular (high/low flow), intramyocardial, adventitial, intratumoral, or intracerebral portion, wound sites, tight joint spaces or body cavity of a human or animal. In certain embodiments, the beneficial agent may be administered locally to avoid or minimize systemic side effects. Gels of the present invention containing a beneficial agent may be injected/implanted directly into or applied as a coating to the desired location, e.g., subcutaneous, intramuscular, intravascular, intramyocardial, adventitial, intratumoral, or intracerebral portion, wound sites, tight joint spaces or body cavity of a human or animal.

[00090] Typically, the viscous gel will be injected from a standard hypodermic syringe, a catheter or a trocar, that has been pre-filled with the beneficial agent-viscous gel composition as the depot. It is often preferred that injections take place using the smallest size needle (i.e., smallest diameter) or catheter to reduce discomfort to the subject when the injection is in a subcutaneous, intramuscular, intravascular (high/low flow), intramyocardial, adventitial, intratumoral, or intracerebral portion, wound sites, tight joint spaces or body cavity of a human or animal. It is desirable to be able to inject gels through a needle or a catheter ranging from 16 gauge and higher, preferably 20 gauge and higher, more preferably 22 gauge and higher, even more preferably 24 gauge and higher. With highly viscous gels, i.e., gels having a viscosity of about 100 poise or greater, injection forces to dispense the gel from a syringe having a needle in the 20-30 gauge range may be so high as to make the injection difficult or reasonably impossible when done manually. At the same time, the high viscosity of the gel is desirable to maintain the integrity of the depot after injection and during the dispensing period and also facilitate desired suspension characteristics of the beneficial agent in the gel.

[00091] A thixotropic gel exhibits reduced viscosity when subjected to shear force. The extent of the reduction is in part a function of the shear rate

of the gel when subjected to the shearing force. When the shearing force is removed, the viscosity of the thixotropic gel returns to a viscosity at or near that which it displayed prior to being subjected to the shearing force.

- Accordingly, a thixotropic gel may be subjected to a shearing force when
5 injected from a syringe or a catheter, which temporarily reduces its viscosity during the injection process. When the injection process is completed, the shearing force is removed and the gel returns very near to its previous state.

- [00092] Significant shear thinning properties of the catheter injectable
10 composition allow for a minimally invasive delivery, via a needle or a catheter, of a beneficial agent to various sites on an external and/or internal surface of the body. Further injection through the needle or injection catheter permits precise administration of a desirable amount of the composition at a desired location, with significant retention of the depot gel composition at the site of
15 delivery while providing for sustained delivery of the beneficial agent from the site of administration. In certain embodiments, the injection catheter may include a metering device or an additional device to assist in the precise delivery of the composition.

- 20 [00093] A composition of a polymer and polymer solvent that optionally includes an agent that imparts thixotropic characteristics to the viscous gel formed by the polymer solvent and polymer provides the desired advantages noted above. It is additionally desirable to use the thixotropic agent in amounts that are sufficiently small so as not to unnecessarily increase the
25 mass and volume of the depot that is to be injected. In this regard it is desirable that the thixotropic agent, i.e. lower alkanols, particularly ethanol, is not a polymer solvent. As is described more fully below, the addition of small amounts of lower alkanols, especially ethanol, to polymer depots formed as viscous gels from biodegradable polymers, preferably lactic acid-based
30 polymers and suitable polymer solvents provide the foregoing desirable characteristics in compositions of the invention described here.

A. The Bioerodible, Biocompatible Polymer:

[00094] Polymers that are useful in conjunction with the methods and compositions of the invention are bioerodible, i.e., they gradually hydrolyze, dissolve, physically erode, or otherwise disintegrate within the aqueous fluids of a patient's body. Generally, the polymers bioerode as a result of hydrolysis or physical erosion, although the primary bioerosion process is typically hydrolysis.

[00095] Such polymers include, but are not limited to, polylactides, polyglycolides, polycaprolactones, polyanhydrides, polyamines, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyphosphoesters, polyoxaesters, polyorthocarbonates, polyphosphazenes, succinates, poly(malic acid), poly(amino acids), polyvinylpyrrolidone, polyethylene glycol, polyhydroxycellulose, chitin, chitosan, hyaluronic acid, and copolymers, terpolymers and mixtures thereof.

[00096] Presently preferred polymers are polylactides, that is, a lactic acid-based polymer that can be based solely on lactic acid or can be a copolymer based on lactic acid, glycolic acid and/or caprolactone, which may include small amounts of other comonomers that do not substantially affect the advantageous results that can be achieved in accordance with the present invention. As used herein, the term "lactic acid" includes the isomers L-lactic acid, D-lactic acid, DL-lactic acid and lactide, while the term "glycolic acid" includes glycolide. Most preferred are polymers selected from the group consisting of polylactide polymers, commonly referred to as PLA, poly(lactide-co-glycolide) copolymers, commonly referred to as PLGA, and poly(caprolactone-co-lactic acid) (PCL-co-LA). The polymer may have a monomer ratio of lactic acid/glycolic acid of from about 100:0 to about 15:85, preferably from about 75:25 to about 30:70, more preferably from about 60:40 to about 40:60, and an especially useful copolymer has a monomer ratio of lactic acid/glycolic acid of about 50:50.

[00097] The poly(caprolactone-co-lactic acid) (PCL-co-LA) polymer has a comonomer ratio of caprolactone/lactic acid of from about 10:90 to about

90:10, from about 50:50; preferably from about 35:65 to about 65:35; and more preferably from about 25:75 to about 75:25. In certain embodiments, the lactic acid based polymer comprises a blend of about 0% to about 90% caprolactone, about 0% to about 100% lactic acid, and about 0% to about 60% glycolic acid.

[00098] The lactic acid-based polymer has a number average molecular weight of from about 1,000 to about 120,000, preferably from about 5,000 to about 50,000, more preferably from about 8,000 to about 30,000, as determined by gel permeation chromatography (GPC). In contrast to prior polymer-based injectable depots, the present invention allows use of higher molecular weight polymers, insofar as the aromatic alcohol of the composition provides excellent shear thinning even with high molecular weight polymers. As indicated in aforementioned U.S. Patent No. 5,242,910, the polymer can be prepared in accordance with the teachings of U.S. Patent No. 4,443,340. Alternatively, the lactic acid-based polymer can be prepared directly from lactic acid or a mixture of lactic acid and glycolic acid (with or without a further comonomer) in accordance with the techniques set forth in U.S. Patent No. 5,310,865. The contents of all of these patents are incorporated by reference. Suitable lactic acid-based polymers are available commercially. For instance, 50:50 lactic acid:glycolic acid copolymers having molecular weights of 8,000, 10,000, 30,000 and 100,000 are available from Boehringer Ingelheim (Petersburg, VA), Medisorb Technologies International L.P. (Cincinnati, OH) and Birmingham Polymers, Inc. (Birmingham, AL) as described below.

[00099] Examples of polymers include, but are not limited to, Poly (D,L-lactide) Resomer[®] L104, PLA-L104, Poly (D,L-lactide-co-glycolide) 50:50 Resomer[®] RG502, Poly (D,L-lactide-co-glycolide) 50:50 Resomer[®] RG502H, Poly (D,L-lactide-co-glycolide) 50:50 Resomer[®] RG503, Poly (D,L-lactide-co-glycolide) 50:50 Resomer[®] RG506, Poly L-Lactide MW 2,000 (Resomer[®] L 206, Resomer[®] L 207, Resomer[®] L 209, Resomer[®] L 214); Poly D,L Lactide (Resomer[®] R 104, Resomer[®] R 202, Resomer[®] R 203, Resomer[®] R 206, Resomer[®] R 207, Resomer[®] R 208); Poly L-Lactide-co-D,L-lactide 90:10

- (Resomer[®] LR 209); Poly glycolide (Resomer[®] G 205); Poly D,L-lactide-co-glycolide 50:50 (Resomer[®] RG 504 H, Resomer[®] RG 504, Resomer[®] RG 505); Poly D,L-lactide-co-glycolide 75:25 (Resomer[®] RG 752, Resomer[®] RG755, Resomer[®] RG 756); Poly D,L-lactide-co-glycolide 85:15 (Resomer[®] RG 858);
- 5 Poly L-lactide-co-trimethylene carbonate 70:30 (Resomer[®] LT 706); Poly dioxanone (Resomer[®] X 210) (Boehringer Ingelheim Chemicals, Inc., Petersburg, VA).

- [000100] Additional examples include, but are not limited to, DL-lactide/glycolide 100:0 (MEDISORB[®] Polymer 100 DL High, MEDISORB[®] Polymer 100 DL Low); DL-lactide/ glycolide 85/15 (MEDISORB[®] Polymer 8515 DL High, MEDISORB[®] Polymer 8515 DL Low); DL-lactide/glycolide 75/25 (MEDISORB[®] Polymer 7525 DL High, MEDISORB[®] Polymer 7525 DL Low); DL-lactide/glycolide 65/35 (MEDISORB[®] Polymer 6535 DL High, MEDISORB[®] Polymer 6535 DL Low);
- 15 DL-lactide/glycolide 54/46 (MEDISORB[®] Polymer 5050 DL High, MEDISORB[®] Polymer 5050 DL Low); and DL-lactide/glycolide 54/46 (MEDISORB[®] Polymer 5050 DL 2A(3), MEDISORB[®] Polymer 5050 DL 3A(3), MEDISORB[®] Polymer 5050 DL 4A(3)) (Medisorb Technologies International L.P., Cincinnati, OH); and Poly D,L-lactide-co-glycolide 50:50; Poly
- 20 D,L-lactide-co-glycolide 65:35; Poly D,L-lactide-co-glycolide 75:25; Poly D,L-lactide-co-glycolide 85:15; Poly DL-lactide; Poly L-lactide; Poly glycolide; Poly ϵ -caprolactone; Poly DL-lactide-co-caprolactone 25:75; and Poly DL-lactide-co-caprolactone 75:25 (Birmingham Polymers, Inc., Birmingham, AL).

- 25 [000101] The biocompatible polymer is present in the gel composition in an amount ranging from about 5 to about 90% by weight, preferably from about 10 to about 85% by weight, preferably from about 15 to about 80% by weight, preferably from about 20 to about 75% by weight, preferably from about 30 to about 70% by weight and typically from about 35 to about 65% by
- 30 weight of the viscous gel, the viscous gel comprising the combined amounts of the biocompatible polymer and a solvent having miscibility in water that is less than 7 wt.% at 25°C. The solvent will be added to polymer in amounts described below, to provide implantable or viscous gels. Again, the

combination of the solvent and the thixotropic agent described herein enables a much wider range of polymer/solvent ratios than obtainable previously.

B. Solvents:


- 5 [000102] The catheter injectable depot composition of the invention contains a water-immiscible solvent having miscibility in water that is less than 7 wt.% at 25°C, in addition to the bioerodible polymer, the thixotropic agent and the beneficial agent. In another embodiment, the catheter injectable depot composition of the invention contains a water-immiscible aromatic alcohol in
10 addition to the bioerodible polymer and the beneficial agent, wherein the composition is free of thixotropic agents such as monohydric lower alkanols. In this embodiment, the aromatic alcohol serves as a solvent and as a thixotropic agent, facilitating solubilization of the bioerodible polymer and also promoting shear thinning behavior upon injection. Preferably the compositions
15 described herein are also free of solvents having miscibility in water that is greater than 7 wt.% at 25°C.

- [000103] The solvent must be biocompatible, should form a viscous gel with the polymer, and restrict water uptake into the implant. Suitable solvents
20 will substantially restrict the uptake of water by the implant and, as noted above, may be characterized as immiscible in water, i.e., having a solubility or miscibility in water of at most 7% by weight. Preferably, the water solubility of the aromatic alcohol is 5 wt.% or less, more preferably 3 wt.% or less, and even more preferably 1 wt.% or less. Most preferably, the solubility of the
25 aromatic alcohol in water is equal to or less than 0.5 weight percent. In preferred embodiments, the solvent is selected from the group consisting of an aromatic alcohol, esters of aromatic acids, aromatic ketones, and mixtures thereof.

- 30 [000104] Water miscibility may be determined experimentally as follows: Water (1-5 g) is placed in a tared clear container at a controlled temperature, about 25°C, and weighed, and a candidate solvent is added dropwise. The solution is swirled to observe phase separation. When the saturation point

appears to be reached, as determined by observation of phase separation, the solution is allowed to stand overnight and is re-checked the following day. If the solution is still saturated, as determined by observation of phase separation, then the percent (w/w) of solvent added is determined. Otherwise
5 more solvent is added and the process repeated. Solubility or miscibility is determined by dividing the total weight of solvent added by the final weight of the solvent/water mixture. When solvent mixtures are used, they are pre-mixed prior to adding to the water.

10 [000105] The aromatic alcohol has the structural formula (I)





wherein Ar is a substituted or unsubstituted aryl or heteroaryl
15 group, n is zero or 1, and L is a linking moiety. Preferably, Ar is a monocyclic aryl or heteroaryl group, optionally substituted with one or more noninterfering substituents such as hydroxyl, alkoxy, thio, amino, halo, and the like. More preferably, Ar is an unsubstituted 5- or 6-membered aryl or heteroaryl group such as phenyl, cyclopentadienyl, pyridinyl, pyrimidinyl, pyrazinyl, pyrrolyl,
20 pyrazolyl, imidazolyl, furanyl, thiophenyl, thiazolyl, isothiazolyl, or the like. The subscript "n" is zero or 1, meaning that the linking moiety L may or may not be present. Preferably, n is 1 and L is generally a lower alkylene linkage such as methylene or ethylene, wherein the linkage may include heteroatoms such as O, N or S. Most preferably, Ar is phenyl, n is 1, and L is methylene, such that
25 the aromatic alcohol is benzyl alcohol.

[000106] The aromatic acid ester or ketone must be biocompatible, should form a viscous gel with the polymer, and restrict water uptake into the implant. Like the aromatic alcohol, suitable aromatic acid esters and ketones will substantially restrict the uptake of water by the implant and, as noted above,
30 may be characterized as immiscible in water, i.e., having a solubility or miscibility in water of at most 7% by weight. Preferably, the water solubility of the solvent alcohol is 5 wt.% or less, more preferably 3 wt.% or less, and even

more preferably 1 wt.% or less. Most preferably, the solubility of the solvent in water is equal to or less than 0.5 weight percent.

[000107] The aromatic acid ester or ketone may be selected from the lower alkyl and aralkyl esters of aromatic acids, and aryl and aralkyl ketones. Generally, although not necessarily, the aromatic acid esters and ketones will respectively have the structural formula (II) or (III)



[000108] In the ester of formula (II), R¹ is substituted or unsubstituted aryl, aralkyl, heteroaryl or heteroaralkyl, preferably substituted or unsubstituted aryl or heteroaryl, more preferably monocyclic or bicyclic aryl or heteroaryl optionally substituted with one or more non-interfering substituents such as hydroxyl, carboxyl, alkoxy, thio, amino, halo, and the like, still more preferably 5- or 6-membered aryl or heteroaryl such as phenyl, cyclopentadienyl, pyridinyl, pyrimidinyl, pyrazinyl, pyrrolyl, pyrazolyl, imidazolyl, furanyl, thiophenyl, thiazolyl, or isothiazolyl, and most preferably 5- or 6-membered aryl. R² is hydrocarbyl or heteroatom-substituted hydrocarbyl, typically lower alkyl or substituted or unsubstituted aryl, aralkyl, heteroaryl or heteroaralkyl, preferably lower alkyl or substituted or unsubstituted aralkyl or heteroaralkyl, more preferably lower alkyl or monocyclic or bicyclic aralkyl or heteroaralkyl optionally substituted with one or more non-interfering substituents such as hydroxyl, carboxyl, alkoxy, thio, amino, halo, and the like, still more preferably lower alkyl or 5- or 6-membered aralkyl or heteroaralkyl, and most preferably lower alkyl or 5- or 6-membered aryl optionally substituted with one or more additional ester groups having the structure -O-(CO)-R¹. Most preferred esters are benzoic acid and phthalic acid derivatives.

[000109] In the ketone of formula (III), R^3 and R^4 may be selected from any of the R^1 and R^2 groups identified above.

[000110] Art recognized benzoic acid derivatives from which solvents having the requisite solubility may be selected include, without limitation: 1,4-cyclohexane dimethanol dibenzoate, diethylene glycol dibenzoate, dipropylene glycol dibenzoate, polypropylene glycol dibenzoate, propylene glycol dibenzoate, diethylene glycol benzoate and dipropylene glycol benzoate blend, polyethylene glycol (200) dibenzoate, isodecyl benzoate, neopentyl glycol dibenzoate, glyceryl tribenzoate, pentaerythritol tetrabenzoate, cumylphenyl benzoate, trimethyl pentanediol dibenzoate.

[000111] Art recognized phthalic acid derivatives from which solvents having the requisite solubility may be selected include: Alkyl benzyl phthalate, bis-cumyl-phenyl isophthalate, dibutoxyethyl phthalate, dimethyl phthalate, dimethyl phthalate, diethyl phthalate, dibutyl phthalate, diisobutyl phthalate, butyl octyl phthalate, diisooheptyl phthalate, butyl octyl phthalate, diisononyl phthalate, nonyl undecyl phthalate, dioctyl phthalate, di-isooctyl phthalate, dicapryl phthalate, mixed alcohol phthalate, di-(2-ethylhexyl) phthalate, linear heptyl, nonyl, phthalate, linear heptyl, nonyl, undecyl phthalate, linear nonyl phthalate, linear nonyl undecyl phthalate, linear dinonyl, didecyl phthalate (diisodecyl phthalate), diundecyl phthalate, ditridecyl phthalate, undecyldodecyl phthalate, decyltridecyl phthalate, blend (50/50) of dioctyl and didecyl phthalates, butyl benzyl phthalate, and dicyclohexyl phthalate.

[000112] Most preferred solvents are derivatives of benzoic acid and include, but are not limited to, methyl benzoate, ethyl benzoate, n-propyl benzoate, isopropyl benzoate, butyl benzoate, isobutyl benzoate, sec-butyl benzoate, tert-butyl benzoate, isoamyl benzoate and benzyl benzoate, with benzyl benzoate being most especially preferred.

[000113] The composition may also include, in addition to the water-immiscible solvent(s), one or more additional miscible solvents ("component

solvents"), provided that any such additional solvent is other than a lower alkanol. Component solvents compatible and miscible with the primary solvent(s) may have a higher miscibility with water and the resulting mixtures may still exhibit significant restriction of water uptake into the implant. Such mixtures will be referred to as "component solvent mixtures." Useful component solvent mixtures may exhibit solubilities in water greater than the primary solvents themselves, typically between 0.1 weight percent and up to and including 50 weight percent, preferably up to and including 30 weight percent, and most preferably up to and including 10 weight percent, without detrimentally affecting the restriction of water uptake exhibited by the implants of the invention.

[000114] Component solvents useful in component solvent mixtures are those solvents that are miscible with the primary solvent or solvent mixture, and include, but are not limited, to triacetin, diacetin, tributyrin, triethyl citrate, tributyl citrate, acetyl triethyl citrate, acetyl tributyl citrate, triethylglycerides, triethyl phosphate, diethyl phthalate, diethyl tartrate, mineral oil, polybutene, silicone fluid, glycerin, ethylene glycol, polyethylene glycol, octanol, ethyl lactate, propylene glycol, propylene carbonate, ethylene carbonate, butyrolactone, ethylene oxide, propylene oxide, N-methyl-2-pyrrolidone, 2-pyrrolidone, glycerol formal, methyl acetate, ethyl acetate, methyl ethyl ketone, dimethylformamide, glycofurol, dimethyl sulfoxide, tetrahydrofuran, caprolactam, decylmethylsulfoxide, oleic acid, and 1-dodecylazacyclo-heptan-2-one, and mixtures thereof.

[000115] The solvent or solvent mixture is capable of dissolving the polymer to form a viscous gel that can maintain particles of the beneficial agent dissolved or dispersed and isolated from the environment of use prior to release. The compositions of the present invention provide implants having a low burst index. Water uptake is controlled by the use of a solvent or component solvent mixture that solublizes or plasticizes the polymer but substantially restricts uptake of water into implant.

[000116] The solvent or solvent mixture is typically present in an amount of from about 95 to about 5% by weight, preferably about 75 to about 15% by weight, and most preferably about 65% to about 20% by weight of the viscous gel. In an especially preferred embodiment, the solvent is selected from an aromatic alcohol, lower alkyl and aralkyl esters of benzoic acid. Presently, the most preferred solvents are benzyl alcohol, benzyl benzoate and the lower alkyl esters of benzoic acid. In certain embodiments, the solvent comprises a mixture of the aromatic alcohol (formula I), aromatic acid ester (formula II) and ketone (formula III). Generally, the weight ratio of the aromatic alcohol to the ester or ketone is in the range of about 1% to about 99%, preferably in the range of about 10% to about 90%, preferably in the range of about 20% to about 80%, preferably in the range of about 25% to about 75%, often in the range of about 25% to about 50%.

[000117] The viscous gel formed by mixing the polymer and the solvent typically exhibits a viscosity of from about 100 to about 200,000 poise, preferably from about 500 to about 50,000 poise, often from about 1,000 to about 50,000 poise measured at a 1 sec^{-1} shear rate and 25°C using a Haake Rheometer at about 1-2 days after mixing is completed. Mixing the polymer with the solvent can be achieved with conventional low shear equipment such as a Ross double planetary mixer for from about 10 minutes to about 1 hour, although shorter and longer periods may be chosen by one skilled in the art depending on the particular physical characteristics of the composition being prepared. Since it may be desirable to administer the implant through an injection catheter as an injectable composition (such as delivered or injected through a needle of the injection catheter), a countervailing consideration when forming implants that are viscous gels is that the polymer, solvent, thixotropic agent and beneficial agent composition have sufficiently low viscosity in order to permit it to be forced through a small needle diameter, e.g., 16 gauge and higher, preferably 20 gauge and higher, more preferably 22 gauge and higher, even more preferably 24 gauge and higher gauge needle or catheter. Significant shear thinning properties of the catheter injectable composition allow for a minimally invasive delivery, via a needle or a catheter,

- of a beneficial agent to various sites on an external and/or internal surface of the body. Further injection through the needle or injection catheter permits precise administration of a desirable amount of the composition at a desired location, with significant retention of the depot gel composition at the site of
- 5 delivery while providing for sustained delivery of the beneficial agent from the site of administration. In certain embodiments, the injection catheter may include a metering device or an additional device to assist in the precise delivery of the composition.
- 10 [000118] The injection catheter comprises a catheter body having an injection needle or delivery channel within the catheter body, for example, extending axially or longitudinally through the catheter body or associated with the catheter body, for example, attached to the catheter body. The needle is retractably movable from the catheter body in order to extend a portion or
- 15 length of the needle from the distal end of the catheter body for delivering or injecting the composition as an implant to a desired site within the subject, such as a specific tissue location within the subject. After delivery of the composition through the needle to the site, the needle is retracted and the composition forms an implant capable of providing sustained release of the
- 20 beneficial agent at the site within the subject. The needle is formed from material including but not limited to, metallic materials, non-metallic materials, ceramic materials, polymeric materials and composites thereof, typically stainless steel, titanium or nickel/ titanium alloys, preferably polymeric in composition including polyurethane, polyimide, polyetheroketone or other
- 25 flexible, non-toxic plastics or composites thereof. Preferably, the catheter body has a length of less than 8 feet; preferably ranging from about 3 feet to about 6 feet, preferably ranging from about 52 inches to about 72 inches; an inner diameter range of less than 2 mm (8F, 0.105"), typically less than 1mm (3F, 0.039"), preferably a range less than 0.8mm (2.4F, 0.032"); and an outer
- 30 diameter range of less than 2 mm (8F, 0.105"), typically less than 1mm (3F, 0.039"), preferably a range less than 0.94 mm (2.8F, 0.037"). If necessary, adjustment of viscosity of the gel for injection can be accomplished with emulsifying agents as described herein. Yet, such compositions should have

adequate dimensional stability so as to remain localized and be able to be removed, if necessary. The particular gel or gel-like compositions of the present invention satisfy such requirements.

5 C. Thixotropic Agents:

[000119] The thixotropic agent, i.e. an agent that imparts thixotropic properties to the polymer gel, is selected from the lower alkanols. Lower alkanol means an alcohol that contains 2-6 carbon atoms and is straight chain or branched chain. Such alcohols may be exemplified by ethanol, isopropanol, and the like. Importantly, such a thixotropic agent is not a polymer solvent. (See e.g., *Development of an in situ forming biodegradable poly-lactide-co-glycolide system for controlled release of proteins*, Lambert, W.J., and Peck, K.D., *Journal of Controlled Release*, 33 (1995) 189-195).

15 [000120] It has been discovered that addition of a thixotropic amount of a thixotropic agent to the polymer solution of the polymer and polymer solvent provides an catheter injectable depot composition having surprisingly substantially significantly improved shear thinning behavior and further reduced injection force as compared to previously described depot
20 compositions. Surprisingly, only a very small amount of thixotropic agent need be added to the polymer solution of the polymer and polymer solvent to obtain the desired reduction in injection force when the gel is dispensed from a syringe. Accordingly, an amount of thixotropic agent that is less than 15% by weight of the combined weight of the polymer solvent and the thixotropic agent
25 has been found to be satisfactory. The thixotropic agent may be present in amounts of 0.01 to 15 weight percent, preferably in amounts of 0.1 to 5 weight percent, and often in amounts of 0.5 to 5 weight percent of the combined weight of the solvent and the thixotropic agent.

30 [000121] It is to be understood that the thixotropic agent of the present invention does not constitute a mere diluent or a polymer-solvent that reduces viscosity by simply decreasing the concentration of the components of the composition. The use of conventional diluents can reduce viscosity, but can

also cause the burst effect mentioned previously when the diluted composition is injected. In contrast, the catheter injectable depot composition of the present invention can be formulated to avoid the burst effect by selecting the thixotropic agent so that once injected into place, the thixotropic agent has little impact on the release properties of the original system. Preferably, the system releases 40% or less by weight of the beneficial agent present in the viscous gel within the first 24 hours after implantation in the subject. More preferably, 30% or less by weight of the beneficial agent will be released within the first 24 hours after implantation, and the implanted composition has a burst index of 12 or less, preferably 8 or less.

D. Beneficial Agents:

[000122] The beneficial agent can be any physiologically or pharmacologically active substance or substances optionally in combination with pharmaceutically acceptable carriers and additional ingredients such as antioxidants, stabilizing agents, permeation enhancers, etc. that do not substantially adversely affect the advantageous results that can be attained by the present invention. The beneficial agent may be any of the agents which are known to be delivered to the body of a human or an animal and that are preferentially soluble in water rather than in the polymer-dissolving solvent. These agents include drug agents, medicaments, vitamins, nutrients, or the like. Included among the types of agents which meet this description are lower molecular weight compounds, proteins, peptides, genetic material, nutrients, vitamins, food supplements, sex sterilants, fertility inhibitors and fertility promoters.

[000123] Drug agents which may be delivered by the present invention include drugs which act on the peripheral nerves, adrenergic receptors, cholinergic receptors, the skeletal muscles, the cardiovascular system, smooth muscles, the blood circulatory system, synaptic sites, neuroeffector junctional sites, endocrine and hormone systems, the immunological system, the reproductive system, the skeletal system, autacoid systems, the alimentary and excretory systems, the histamine system and the central nervous system.

Suitable agents may be selected from, for example, a drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-
5 inflammatory agents including anti-inflammatory corticosteroids, antiproliferative agents, antimitotic agents, angiogenic agents, anticoagulants, fibrinolytic agents, growth factors, antibodies, ocular drugs, and metabolites, analogs (including synthetic and substituted analogs), derivatives (including aggregative conjugates/fusion with other macromolecules and covalent
10 conjugates with unrelated chemical moieties by means known in the art) fragments, and purified, isolated, recombinant and chemically synthesized versions of these species.

[000124] Examples of drugs that may be delivered by the composition of
15 the present invention include, but are not limited to, procaine, procaine hydrochloride, tetracaine, tetracaine hydrochloride, cocaine, cocaine hydrochloride, chlorprocaine, chlorprocaine hydrochloride, proparacaine, proparacaine hydrochloride, piperocaine, piperocaine hydrochloride, hexylcaine, hexylcaine hydrochloride, naepaine, naepaine hydrochloride,
20 benzoxinate, benzoxinate hydrochloride, cyclomethylcaine, cyclomethylcaine hydrochloride, cyclomethylcaine sulfate, lidocaine, lidocaine hydrochloride, bupivacaine, bupivacaine hydrochloride, mepivacaine, mepivacaine hydrochloride, prilocaine, prilocaine hydrochloride, dibucaine and dibucaine hydrochloride, etidocaine, benzocaine, propoxycaine, dyclonin, pramoxine,
25 oxybuprocaine, prochlorperzine edisylate, ferrous sulfate, aminocaproic acid, mecamlamine hydrochloride, procainamide hydrochloride, amphetamine sulfate, methamphetamine hydrochloride, benzamphetamine hydrochloride, isoproterenol sulfate, phenmetrazine hydrochloride, bethanechol chloride, methacholine chloride, pilocarpine hydrochloride, atropine sulfate,
30 scopolamine bromide, isopropamide iodide, tridihexethyl chloride, phenformin hydrochloride, methylphenidate hydrochloride, theophylline choline, cephalixin hydrochloride, diphenidol, meclizine hydrochloride, prochlorperazine maleate, phenoxybenzamine, thiethylperzine maleate,

- anisindone, diphenadione erythryl tetranitrate, digoxin, isofluorophate, acetazolamide, methazolamide, bendroflumethiazide, chlorpromazine, tolazamide, chlormadinone acetate, phenaglycodol, allopurinol, aluminum aspirin, methotrexate, acetyl sulfisoxazole, erythromycin, hydrocortisone,
- 5 hydrocorticosterone acetate, cortisone acetate, dexamethasone and its derivatives such as betamethasone, triamcinolone, methyltestosterone, 17-S-estradiol, ethinyl estradiol, ethinyl estradiol 3-methyl ether, prednisolone, 17 α -hydroxyprogesterone acetate, 19-nor-progesterone, norgestrel, norethindrone, norethisterone, norethiederone, progesterone, norgesterone, norethynodrel,
- 10 aspirin, indomethacin, naproxen, fenoprofen, sulindac, indoprofen, nitroglycerin, isosorbide dinitrate, propranolol, timolol, atenolol, alprenolol, cimetidine, clonidine, imipramine, levodopa, chlorpromazine, methyl dopa, dihydroxyphenylalanine, theophylline, calcium gluconate, ketoprofen, ibuprofen, cephalexin, erythromycin, haloperidol, zomepirac, ferrous lactate,
- 15 vincamine, diazepam, phenoxybenzamine, diltiazem, milrinone, mandol, quanbenz, hydrochlorothiazide, ranitidine, flurbiprofen, fenufen, fluprofen, tolmetin, alclofenac, mefenamic, flufenamic, difuinal, nimodipine, nitrendipine, nisoldipine, nicardipine, felodipine, lidoflazine, tiapamil, gallopamil, amlodipine, mioflazine, lisinopril, enalapril, enalaprilat, captopril, ramipril, famotidine,
- 20 nizatidine, sucralfate, etintidine, tetratolol, minoxidil, chlordiazepoxide, diazepam, amitriptyline, and imipramine. Further examples are proteins and peptides which include, but are not limited to, bone morphogenic proteins, insulin, colchicine, glucagon, thyroid stimulating hormone, parathyroid and pituitary hormones, calcitonin, renin, prolactin, corticotrophin, thyrotropic
- 25 hormone, follicle stimulating hormone, chorionic gonadotropin, gonadotropin releasing hormone, bovine somatotropin, porcine somatotropin, oxytocin, vasopressin, GRF, somatostatin, lypressin, pancreozymin, luteinizing hormone, LHRH, LHRH agonists and antagonists, leuprolide, interferons such as interferon alpha-2a, interferon alpha-2b, and consensus interferon,
- 30 interleukins, growth factors such as epidermal growth factors (EGF), platelet-derived growth factors (PDGF), fibroblast growth factors (FGF), transforming growth factors- α (TGF- α), transforming growth factors- β (TGF- β), erythropoietin (EPO), insulin-like growth factor-I (IGF-I), insulin-like growth

factor-II (IGF-II), interleukin-1, interleukin-2, interleukin-6, interleukin-8, tumor necrosis factor- α (TNF- α), tumor necrosis factor- β (TNF- β), Interferon- α (INF- α), Interferon- β (INF- β), Interferon- γ (INF- γ), Interferon- ω (INF- ω), colony stimulating factors (CGF), vascular cell growth factor (VEGF), thrombopoietin (TPO), stromal cell-derived factors (SDF), placenta growth factor (PIGF), hepatocyte growth factor (HGF), granulocyte macrophage colony stimulating factor (GM-CSF), glial-derived neurotrophin factor (GDNF), granulocyte colony stimulating factor (G-CSF), ciliary neurotrophic factor (CNTF), bone morphogeneic proteins (BMP), coagulation factors, human pancreas hormone releasing factor, analogs and derivatives of these compounds, and pharmaceutically acceptable salts of these compounds, or their analogs or derivatives.

[000125] Additional examples of drugs that may be delivered by the composition of the present invention include, but are not limited to, antiproliferative/antimitotic agents including natural products such as vinca alkaloids (i.e. vinblastine, vincristine, and vinorelbine), paclitaxel, epidipodophyllotoxins (i.e. etoposide, teniposide), antibiotics (dactinomycin, actinomycin D, daunorubicin, doxorubicin and idarubicin), anthracyclines, mitoxantrone, bleomycins, plicamycin (mithramycin) and mitomycin, enzymes (L-asparaginase which systemically metabolizes L-asparagine and deprives cells which do not have the capacity to synthesize their own asparagine); antiplatelet agents such as G(GP)II_bIII_a inhibitors and vitronectin receptor antagonists; antiproliferative/antimitotic alkylating agents such as nitrogen mustards (mechlorethamine, cyclophosphamide and analogs, melphalan, chlorambucil), ethylenimines and methylmelamines (hexamethylmelamine and thiotepa), alkyl sulfonates-busulfan, nirtosoureas (carmustine (BCNU) and analogs, streptozocin), trazenes - dacarbazine (DTIC); antiproliferative/antimitotic antimetabolites such as folic acid analogs (methotrexate), pyrimidine analogs (fluorouracil, floxuridine, and cytarabine), purine analogs and related inhibitors (mercaptopurine, thioguanine, pentostatin and 2-chlorodeoxyadenosine (cladribine)); platinum coordination complexes (cisplatin, carboplatin), procarbazine, hydroxyurea, mitotane,

aminoglutethimide; hormones (i.e. estrogen); anticoagulants (heparin, synthetic heparin salts and other inhibitors of thrombin); fibrinolytic agents (such as tissue plasminogen activator, streptokinase and urokinase), aspirin, dipyridamole, ticlopidine, clopidogrel, abciximab; antimigratory; antisecretory
5 (breveldin); antiinflammatory: such as adrenocortical steroids (cortisol, cortisone, fludrocortisone, prednisone, prednisolone, 6 α -methylprednisolone, triamcinolone, betamethasone, and dexamethasone), non-steroidal agents (salicylic acid derivatives i.e. aspirin; para-aminophenol derivatives i.e. acetaminophen); indole and indene acetic acids (indomethacin, sulindac, and
10 etodolac), heteroaryl acetic acids (tolmetin, diclofenac, and ketorolac), arylpropionic acids (ibuprofen and derivatives), anthranilic acids (mefenamic acid, and meclofenamic acid), enolic acids (piroxicam, tenoxicam, phenylbutazone, and oxyphenbutazone), nabumetone, gold compounds (auranofin, aurothioglucose, gold sodium thiomalate); immunosuppressives:
15 (cyclosporine, tacrolimus (FK-506), sirolimus (rapamycin), azathioprine, mycophenolate mofetil); angiogenic agents: vascular endothelial growth factor (VEGF), fibroblast growth factor (FGF); angiotensin receptor blocker, nitric oxide donors; anti-sense oligonucleotides and combinations thereof; cell cycle inhibitors, mTOR inhibitors, and growth factor signal transduction kinase
20 inhibitors, analogs and derivatives of these compounds, and pharmaceutically acceptable salts of these compounds, or their analogs or derivatives.

[000126] In certain preferred embodiments, the beneficial agent includes chemotactic growth factors, proliferative growth factors, stimulatory growth
25 factors, and transformational peptide growth factors including genes, precursors, post-translational-variants, metabolites, binding-proteins, receptors, receptor agonists and antagonists of the following growth factor families: epidermal growth factors (EGFs), platelet-derived growth factor (PDGFs), insulin-like growth factors (IGFs), fibroblast-growth factors (FGFs),
30 transforming-growth factors (TGFs), interleukins (ILs), colony-stimulating factors (CSFs, MCFs, GCSFs, GMCSFs), Interferons (IFNs), endothelial growth factors (VEGF, EGFs), erythropoietins (EPOs), angiopoietins (ANGs),

placenta-derived growth factors (PIGFs), and hypoxia induced transcriptional regulators (HIFs).

[000127] The present invention also finds application with
5 chemotherapeutic agents for the local application of such agents to avoid or
minimize systemic side effects. Gels of the present invention containing
chemotherapeutic agents may be injected directly into the tumor tissue for
sustained delivery of the chemotherapeutic agent over time. In some cases,
particularly after resection of the tumor, the gel may be implanted directly into
10 the resulting cavity or may be applied to the remaining tissue as a coating. In
cases in which the gel is implanted after surgery, it is possible to utilize gels
having higher viscosities since they do not have to pass through a small
diameter needle. Representative chemotherapeutic agents that may be
delivered in accordance with the practice of the present invention include, for
15 example, carboplatin, cisplatin, paclitaxel, BCNU, vincristine, camptothecin,
etoposide, cytokines, ribozymes, interferons, oligonucleotides and
oligonucleotide sequences that inhibit translation or transcription of tumor
genes, functional derivatives of the foregoing, and generally known
chemotherapeutic agents such as those described in U.S. Patent 5,651,986.
20 The present application has particular utility in the sustained delivery of water
soluble chemotherapeutic agents, such as for example cisplatin and
carboplatin and the water soluble derivatives of paclitaxel. Those
characteristics of the invention that minimize the burst effect are particularly
advantageous in the administration of water soluble beneficial agents of all
25 kinds, but particularly those compounds that are clinically useful and effective
but may have adverse side effects.

[000128] To the extent not mentioned above, the beneficial agents
described in aforementioned U.S. Patent No. 5,242,910 can also be used.
30 One particular advantage of the present invention is that materials, such as
proteins, as exemplified by the enzyme lysozyme, and cDNA, and DNA
incorporated into vectors both viral and nonviral, which are difficult to
microencapsulate or process into microspheres can be incorporated into the

compositions of the present invention without the level of degradation caused by exposure to high temperatures and denaturing solvents often present in other processing techniques.

5 [000129] The beneficial agent is preferably incorporated into the viscous gel formed from the polymer and the solvent in the form of particles typically having an average particle size of from about 0.1 to about 250 microns, preferably from about 1 to about 200 microns and often from 30 to 125
10 microns. For instance, particles having an average particle size of about 5 microns have been produced by spray drying or freeze drying an aqueous mixture containing 50% sucrose and 50% chicken lysozyme (on a dry weight basis) and mixtures of 10-20% hGH and 15-30 mM zinc acetate. Such particles have been used in certain of the examples illustrated in the figures. Conventional lyophilization processes can also be utilized to form particles of
15 beneficial agents of varying sizes using appropriate freezing and drying cycles.

[000130] To form a suspension or dispersion of particles of the beneficial agent in the viscous gel formed from the polymer and the solvent, any conventional low shear device can be used such as a Ross double planetary
20 mixer at ambient conditions. In this manner, efficient distribution of the beneficial agent can be achieved substantially without degrading the beneficial agent.

[000131] The beneficial agent is typically dissolved or dispersed in the
25 composition in an amount of from about 0.1% to about 50% by weight, preferably in an amount of from about 1% to about 40%, more preferably in an amount of about 2% to about 30%, and often 2 to 20% by weight of the combined amounts of the polymer, solvent, and beneficial agent. Depending on the amount of beneficial agent present in the composition, one can obtain
30 different release profiles and burst indices. More specifically, for a given polymer and solvent, by adjusting the amounts of these components and the amount of the beneficial agent, one can obtain a release profile that depends more on the degradation of the polymer than the diffusion of the beneficial

agent from the composition or vice versa. In this respect, at lower beneficial agent loading rates, one generally obtains a release profile reflecting degradation of the polymer wherein the release rate increases with time. At higher loading rates, one generally obtains a release profile caused by

5 diffusion of the beneficial agent wherein the release rate decreases with time. At intermediate loading rates, one obtains combined release profiles so that if desired, a substantially constant release rate can be attained. In order to minimize burst, loading of beneficial agent on the order of 30% or less by weight of the overall gel composition, i.e., polymer, solvent and beneficial

10 agent, is preferred, and loading of 20% or less is more preferred.

[000132] Release rates and loading of beneficial agent will be adjusted to provide for therapeutically effective delivery of the beneficial agent over the intended sustained delivery period. Preferably, the beneficial agent will be

15 present in the polymer gel at concentrations that are above the saturation concentration of beneficial agent in water to provide a drug reservoir from which the beneficial agent is dispensed. While the release rate of beneficial agent depends on the particular circumstances, such as the beneficial agent to be administered, release rates on the order of from about 0.1 micrograms/day

20 to about 30 milligrams/day, preferably from about 1 microgram/day to about 20 milligrams per day, more preferably from about 10 micrograms/day to about 10 milligram/day, for periods of from about 24 hours to about 180 days, preferably 24 hours to about 120 days, more preferably 24 hours to about 90 days, often 3 days to about 90 days can be obtained.

25

[000133] Further, the dose of beneficial agent may be adjusted by adjusting the amount of depot gel injected. Greater amounts may be delivered if delivery is to occur over shorter periods. Generally, higher release rate is possible if a greater burst can be tolerated. In instances where the gel

30 composition is surgically implanted, or used as a "leave behind" depot when surgery to treat the disease state or another condition is concurrently conducted, it is possible to provide higher doses that would normally be administered if the implant was injected. Further, the dose of beneficial agent

- may be controlled by adjusting the volume of the gel implanted or the catheter injectable gel injected. Preferably, the system releases 40% or less by weight of the beneficial agent present in the viscous gel within the first 24 hours after implantation in the subject. More preferably, 30% or less by weight of the
- 5 beneficial agent will be released within the first 24 hours after implantation, and the implanted composition has a burst index of 12 or less, preferably 8 or less.

E. Optional Additional Components:

- 10 [000134] Other components may be present in the gel composition, to the extent they are desired or provide useful properties to the composition, such as polyethylene glycol, hydroscopic agents, stabilizing agents (for example surfactants like tween 20, tween 80, and the like, sugars such as sucrose, trehalose, and the like, salts, antioxidants), pore forming agents, bulking
- 15 agents (such as sorbitol, mannitol, glycine, and the like), chelating agents (such as divalent metal ions including zinc, magnesium, calcium, copper and the like), buffering agents (such as phosphate, acetate, succinate, histidine, TRIS, and the like) and others. When the composition includes a peptide or a protein that is soluble in or unstable in an aqueous environment, it may be
- 20 highly desirable to include a solubility modulator that may, for example, be a stabilizing agent, in the composition. Various modulating agents are described in U.S. Patent Nos. 5,654,010 and 5,656,297, the disclosures of which are incorporated herein by reference. In the case of hGH, for example, it is preferable to include an amount of a salt of a divalent metal, preferably zinc.
- 25 Examples of such modulators and stabilizing agents, which may form complexes with the beneficial agent or associate to provide the stabilizing or modulated release effect, include metal cations, preferably divalent, present in the composition as magnesium carbonate, zinc carbonate, calcium carbonate, magnesium acetate, magnesium sulfate, zinc acetate, zinc sulfate, zinc
- 30 chloride, magnesium chloride, magnesium oxide, magnesium hydroxide, other antacids, and the like. The amounts of such agents used will depend on the nature of the complex formed, if any, or the nature of the association between the beneficial agent and the agent. Molar ratios of solubility modulator or

stabilizing agent to beneficial agent of about 100:1 to 1:1, preferably 10:1 to 1:1, typically can be utilized.

5 [000135] Pore forming agents include biocompatible materials that when contacted with body fluids dissolve, disperse or degrade to create pores or channels in the polymer matrix. Typically, organic and non-organic materials that are water soluble such as sugars (e.g., sucrose, dextrose), water soluble salts (e.g., sodium chloride, sodium phosphate, potassium chloride, and sodium carbonate), water soluble solvents such as N-methyl-2-pyrrolidone and
10 polyethylene glycol and water soluble polymers (e.g., carboxymethylcellulose, hydroxypropyl-cellulose, and the like) can conveniently be used as pore formers. Such materials may be present in amounts varying from about 0.1% to about 100% of the weight of the polymer, but will typically be less than 50% and more typically less than 10-20% of the weight of polymer.

15

II. Utility and Administration:

[000136] The means of administration of the implants is not limited to injection, although that mode of delivery may often be preferred. Where the implant will be administered as a leave-behind product, it may be formed to fit
20 into a body cavity existing after completion of surgery or it may be applied as a flowable gel by brushing or palleting the gel onto residual tissue or bone. Such applications may permit loading of beneficial agent in the gel above concentrations typically present with catheter injectable compositions.

25 [000137] Compositions of this invention without beneficial agent are useful for wound healing, bone repair and other structural support purposes.

[000138] To further understand the various aspects of the present invention, the results set forth in the previously described figures were
30 obtained in accordance with the following examples.

EXAMPLE 1

[000139] A gel vehicle for use in a catheter injectable depot of the composition was prepared as follows. A glass vessel was tared on a Mettler

- PJ3000 top loader balance. Poly (D,L-lactide-co-glycolide) (PLGA), available as 50:50 Resomer[®] RG502 (PLGA RG 502), was weighed into the glass vessel. The glass vessel containing PLGA was tared and the corresponding solvent was added. Amounts expressed as percentages for various
- 5 polymer/solvent combinations are set forth in Table 1, below. The polymer/solvent mixture was manually stirred with a stainless steel square-tip spatula, resulting in a sticky amber paste-like substance containing white polymer particles. The vessel containing the polymer/solvent mixture was sealed and placed in a temperature controlled incubator equilibrated to 39°C.
- 10 The polymer/solvent mixture was removed from the incubator when it appeared to be a clear amber homogeneous gel. Incubation time intervals ranged from 1 to 4 days, depending on solvent and polymer type and solvent and polymer ratios. Thereafter, the mixture was placed in an oven (65°C) for 30 minutes. It was noted that the PLGA-504 was dissolved in the mixture
- 15 upon removal from the oven.

- [000140] Additional depot gel vehicles are prepared with the following solvents or mixtures: benzyl benzoate, benzyl alcohol, propylene glycol, and ethanol and the following polymers: Poly (D,L-lactide) Resomer[®] L104, PLA-
- 20 L104, Poly (D,L-lactide-co-glycolide) 50:50 Resomer[®] RG502, Poly (D,L-lactide-co-glycolide) 50:50 Resomer[®] RG502H, Poly (D,L-lactide-co-glycolide) 50:50 Resomer[®] RG503, Poly L-Lactide MW 2,000 (Resomer[®] L 206, Resomer[®] L 207, Resomer[®] L 209, Resomer[®] L 214); Poly D,L Lactide (Resomer[®] R 104, Resomer[®] R 202, Resomer[®] R 203, Resomer[®] R 206,
- 25 Resomer[®] R 207, Resomer[®] R 208); Poly L-Lactide-co-D,L-lactide 90:10 (Resomer[®] LR 209); Poly D-L-lactide-co-glycolide 75:25 (Resomer[®] RG 752, Resomer[®] RG755, Resomer[®] RG 756); Poly D,L-lactide-co-glycolide 85:15 (Resomer[®] RG 858); Poly L-lactide-co-trimethylene carbonate 70:30 (Resomer[®] LT 706); Poly dioxanone (Resomer[®] X 210) (Boehringer Ingelheim
- 30 Chemicals, Inc., Petersburg, VA); DL-lactide/glycolide 100:0 (MEDISORB[®] Polymer 100 DL High, MEDISORB[®] Polymer 100 DL Low); DL-lactide/glycolide 85/15 (MEDISORB[®] Polymer 8515 DL High, MEDISORB[®] Polymer 8515 DL Low); DL-lactide/glycolide 75/25 (MEDISORB[®] Polymer 7525 DL

High, MEDISORB® Polymer 7525 DL Low); DL-lactide/glycolide 65/35 (MEDISORB® Polymer 6535 DL High, MEDISORB® Polymer 6535 DL Low); DL-lactide/glycolide 54/46 (MEDISORB® Polymer 5050 DL High, MEDISORB® Polymer 5050 DL Low); and DL-lactide/glycolide 54/46 (MEDISORB® Polymer 5050 DL 2A(3), MEDISORB® Polymer 5050 DL 3A(3), MEDISORB® Polymer 5050 DL 4A(3)) (Medisorb Technologies International L.P., Cincinnati, OH); and Poly D,L-lactide-co-glycolide 50:50; Poly D,L-lactide-co-glycolide 65:35; Poly D,L-lactide-co-glycolide 75:25; Poly D,L-lactide-co-glycolide 85:15; Poly DL-lactide; Poly L-lactide; Poly glycolide; Poly ε-caprolactone; Poly DL-lactide-co-caprolactone 25:75; and Poly DL-lactide-co-caprolactone 75:25 (Birmingham Polymers, Inc., Birmingham, AL). Representative gel vehicles are described in Table 1 below.

Table 1

Formulation	Polymer gm (%)	Benzyl Benzoate gm (%)	Benzyl Alcohol gm (%)	Propylene Glycol gm (%)
1	5.0365	4.5093	0.5178	-
2	5.0139	3.7553	1.2560	-
3	5.0350	4.5193	-	0.5206
4	5.0024	3.7547	-	1.2508
5	5.0068	5.0044	-	-

Example 2

[000141] Rheological behavior was tested for depot vehicles formulated with different solvents. A vehicle comprising 50 wt.% polymer (PLGA RG502) and 50 wt.% solvent (benzyl alcohol) was prepared according to the procedures outlined in Example 1. For comparative purposes, solvent comprising benzyl benzoate (e.g., formulation 5) or benzyl benzoate combined with ethanol (e.g., formulation 7) were also prepared. Table 2 lists the formulations used in the test.

Table 2

Formulation	Polymer (%)	Benzyl Benzoate (%)	Benzyl Alcohol (%)	Ethanol (%)
5	50.0	50.0	0.0	0.0
6	50.0	0.0	50.0	0.0
7	45.0	52.8	0.0	2.2

5 [000142] Formulations 5, 6 and 7 were tested for viscosity under various shear rates. As indicated in Figure 1, significant shear thinning behavior was observed when benzyl alcohol was used as the solvent (e.g., formulation 6), in contrast to formulations using benzyl benzoate (e.g., formulation 5) and benzyl benzoate with ethanol as a thixotropic agent (e.g., formulation 7), respectively.

10

Example 3

[000143] The injection force required to dispense depot vehicles was evaluated for the three formulations identified in Example 2. The formulations were injected through a 24-gauge needle at 1 ml/minute, at room temperature.

15 As indicated in Figure 2, significantly reduced injection force was observed when benzyl alcohol is used as the solvent (e.g., formulation 6), in contrast to formulations using benzyl benzoate (e.g., formulation 5) and benzyl benzoate with ethanol as a thixotropic agent (e.g., formulation 7), respectively. Notably, due to the shear thinning behavior, the formulations using benzyl alcohol as the

20 solvent (e.g., formulation 6), and benzyl benzoate with ethanol as a thixotropic agent (e.g., formulation 7) showed significantly reduced injection force while maintaining viscosities equal to or greater than the formulations using benzyl benzoate (e.g., formulation 5), at lower shear rate; thus maintaining the intactness of the depot after injection into the animals.

25

Example 4.

[000144] The injection force required to dispense depot vehicles was evaluated for a series of vehicles. Formulations containing PLGA RG502 at

30 various weight percents were each combined with solvents as follows: 100% benzyl benzoate; 75 wt.% benzyl benzoate, 25 wt.% benzyl alcohol; and 100%

benzyl alcohol. The amount of the solvent was added to bring the total amount of the formulation to 100%, e.g., if PLGA-502 was used at 45 wt.%, 55 wt.% of the solvent was used. The formulations were then tested for the injection force necessary to pass the formulation through a 24-gauge needle at 1 ml/minute, at room temperature. As seen in Figure 3, benzyl alcohol offers flexibility for depot vehicle formulation, thereby enabling the formulation of depot vehicles with much higher PLGA molecular weights while maintaining reasonably low injection force as compared to similar benzyl benzoate-containing formulations. Furthermore, for any given percentage of PLGA-502 in the formulation, the injection force decreases as the percentage of the benzyl alcohol increases, as illustrated in Figure 4.

Example 5

[000145] Rheological behavior was tested for depot vehicles formulated with the ethanol as a thixotropic agent alone with benzyl alcohol as described in this invention. The vehicle formulations comprising 50 wt.% polymer (PLGA RG502) and benzyl alcohol as the solvent with 5 and 10% ethanol as a thixotropic agent (e.g., formulations 9 and 10), respectively, were prepared according to the procedures outlined in Example 1. For comparative purposes, solvent comprising only benzyl alcohol (e.g., formulation 8) was also prepared. Table 3 lists the formulations used in the test. Formulations 8, 9 and 10 were tested for viscosity under various shear rates. As indicated in Figure 5, more significant shear thinning behavior was observed when ethanol was used as a thixotropic agent together with the solvent benzyl alcohol (e.g., formulations 9 & 10), as compared to the formulation using benzyl alcohol alone (e.g., formulation 8).

Table 3

Formulation	Polymer (%) ¹	Benzyl Benzoate (%)	Benzyl Alcohol (%)	Ethanol (%)
8	50.0	0.0	50.0	0.0
9	50.0	0.0	47.5	2.5
10	50.0	0.0	45.0	5.0

1 = PLGA RG502 polymer (MW 16,000)

Example 6

5 **[000146]** The injection force required to dispense depot vehicles was evaluated for the three formulations identified in Example 5. The formulations were injected through a 24-gauge needle at 1 ml/minute, at room temperature. As indicated in Figure 6, further reduced injection force was observed when ethanol is used as a thixotropic agent together with the solvent benzyl alcohol,
10 as compared to formulations using benzyl alcohol alone (e.g., formulation 8).

Example 7

15 **[000147]** Rheological behavior was tested for depot vehicles formulated with ethanol as a thixotropic agent together with the mixture of benzyl benzoate and benzyl alcohol as described in this invention. The vehicle formulations comprising 50 wt.% polymer (PLGA RG502) and the mixture of benzyl benzoate and benzyl alcohol as the solvent with 5 and 10% ethanol as a thixotropic agent (e.g., formulations 12 - 15), respectively, were prepared
20 according to the procedures outlined in Example 1. For comparative purposes, the mixture of solvent without ethanol as a thixotropic agent (e.g., formulation 11) was also prepared. Table 4 lists the formulations used in the test.

25 **[000148]** Formulations 11 - 15 were tested for viscosity under various shear rates. As indicated in Figures 7 and 8, more significant shear thinning behavior was observed when ethanol was used as a thixotropic agent together with the mixture of benzyl benzoate and benzyl alcohol as solvent (e.g., formulations 12 & 13 in Figure 7 and formulation 14 & 15 in Figure 8), as
30 compared to the formulation using the mixture of benzyl benzoate and benzyl alcohol without ethanol as a thixotropic agent (e.g., formulation 11).

Table 4

Formulation	Polymer (%) ¹	Benzyl Benzoate (%)	Benzyl Alcohol (%)	Ethanol (%)
11	50.0	37.5	12.5	0.0
12	50.0	35.6	11.9	2.5
13	50.0	33.7	11.3	5.0
14	50.0	37.5	10.0	2.5
15	50.0	37.5	7.5	5.0

1 = PLGA RG502 polymer (MW 16,000).

5

Example 8

[000149] The injection force required to dispense depot vehicles was evaluated for the three formulations identified in Example 7. The formulations were injected through a 24-gauge needle at 1 ml/minute, at room temperature. As indicated in Figures 9 and 10, further reduced injection force was observed when ethanol is used as a thixotropic agent together with the mixture of benzyl benzoate and benzyl alcohol as the solvent (e.g., formulations 12 & 13 in Figure 9 and formulations 14 & 15 in Figure 10), as compared to the formulation using the mixture without ethanol as a thixotropic agent (e.g., formulation 11). Due to the shear thinning behavior the formulations with benzyl alcohol as a solvent and/or ethanol as a thixotropic agent showed significantly reduced injection force while maintaining equal to or greater than the formulations with benzyl benzoate alone at lower shear rate; thus maintaining the intactness of the depot after injection into the animals.

20

Example 9hGH Particle Preparation

25 [000150] Human growth hormone (hGH) particles (optionally containing zinc acetate) were prepared as follows:

hGH solution (5 mg/ml) solution in water (BresaGen Corporation, Adelaide, Australia) was concentrated to 10 mg/mL using a Concentration/Dialysis Selector diafiltering apparatus. The diafiltered hGH solution was washed with 5 times volume of tris or phosphate buffer solution (pH 7.6).

30

Particles of hGH were then formed by spray drying or lyophilization using conventional techniques. Phosphate buffer solutions (5 or 50 mM) containing hGH (5 mg/mL) (and optionally various levels of zinc acetate (0 to 30 mM) when Zn complexed particles were prepared) were spray-dried using a

- 5 Yamato Mini Spray dryer set at the following parameters:

Spray Dryer Parameter	Setting
Atomizing Air	2 psi
Inlet Temperature	120°C
Aspirator Dial	7.5
Solution Pump	2-4
Main Air Valve	40-45 psi

- [000151] Lyophilized particles were prepared from tris buffer solutions (5 or 50 mM: pH 7.6) containing hGH (5 mg/mL) using a Durastop μ P Lyophilizer
- 10 in accordance with the following freezing and drying cycles:

Freezing cycle	Ramp down at 2.5 C/min to -30° C and hold for 30 min
	Ramp down at 2.5 C/min to -30° C and hold for 30 min
Drying cycle	Ramp up at 0.5 C/min to 10° C and hold for 960 min
	Ramp up at 0.5 C/min to 20° C and hold for 480 min
	Ramp up at 0.5 C/min to 25° C and hold for 300 min
	Ramp up at 0.5 C/min to 30° C and hold for 300 min
	Ramp up at 0.5 C/min to 5° C and hold for 5000 min

Example 10

HGH-Stearic Acid Particle Preparation

- [000152] Human growth hormone (hGH) particles were prepared as follows: Lyophilized hGH (3.22 grams, Pharmacia-Upjohn, Stockholm, Sweden) and stearic acid (3.22 grams, 95% pure, Sigma-Aldrich Corporation, St. Louis, MO) were blended and ground. The ground material was
- 20 compressed in a 13 mm round die, with a force of 10,000 pounds for 5 minutes. Compressed tablets were ground and sieved through a 70 mesh screen followed by a 400 mesh screen to obtain particles having a size range between 38 - 212 microns.

Example 11Bupivacaine-Stearic Acid Particle Preparation

[000153] Bupivacaine particles were prepared as follows: Bupivacaine hydrochloride (100 grams, Sigma-Aldrich Corporation, St. Louis, MO) was and sieved through 63 -125 micron sieves. The bupivacaine particles and stearic acid (100 grams, 95% pure, Sigma-Aldrich Corporation, St. Louis, MO) were blended and ground. The ground material was compressed in a 13 mm round die, with a force of 5,000 pounds for 5 minutes. Compressed tablets were ground and sieved through a 120 mesh screen followed by a 230 mesh screen to obtain particles having a size range between 63 - 125 microns.

Example 12Drug Loading

[000154] Compressed particles comprising beneficial agent/stearic acid prepared as above are added to a gel vehicle in an amount of 10 - 20 % by weight and blended manually until the dry powder is wetted completely. Then, the milky light yellow particle/gel mixture is thoroughly blended by conventional mixing using a Caframo mechanical stirrer with an attached square-tip metal spatula. Resulting formulations are illustrated in Table 5 below. Final homogenous gel formulations were transferred to 3, 10 or 30 cc disposable syringes for storage or dispensing.

Table 5

Formulation	Polymer (%)	Benzyl Benzoate (%)	Benzyl Alcohol (%)	Ethanol (%)
16 ^a	45.0 ¹	45.0	0.0	0.0
17 ^a	39.6 ¹	49.5	0.0	0.9
18 ^a	45.0 ¹	33.8	11.3	0.0
19 ^a	45.0 ²	33.8	11.3	0.0
20 ^b	58.5 ³	31.5	0.0	0.0
21 ^b	58.5 ³	0.0	31.5	0.0
22 ^b	67.5 ³	0.0	22.5	0.0
23 ^b	67.5 ⁴	0.0	22.5	0.0
24 ^c	60.0 ⁴	0.0	20.0	0.0
25 ^a	45.0 ¹	0.0	45.0	0.0

- 1 = PLGA RG-502 polymer (MW 16,000);
2 = PLGA- L/G 50/50 polymer (MW 22,600);
3 = PLGA L/G 50/50 with ester end group (MW 8,000);
4 = PLGA L/G 50/50 with acid end group (MW 10,000);
5 a = 5% hGH, 5% SA;
b = 10% bupivacaine;
c = 10% bupivacaine, 10% SA.

[000155] A representative number of implantable gels were prepared in accordance with the foregoing procedures and tested for *in vitro* release of beneficial agent as a function of time and also in *in vivo* studies in rats to determine release of the beneficial agent as determined by blood serum or plasma concentrations of beneficial agent as a function of time.

Example 13

hGH In Vivo Studies

[000156] *In vivo* studies in rats were performed following an open protocol to determine serum levels of hGH upon systemic administration of hGH via the implant systems of this invention. Depot gel hGH formulations were loaded into customized 0.5 cc disposable syringes. Disposable 18 gauge 1" needles were attached to the syringes and were heated to 37°C using a circulator bath. Depot gel hGH formulations were injected into immunosuppressed rats and serum samples were collected post - injection at 1hr, 4 hr, day 1, 2, 4, 7, 10, 14; 21 and 28. All serum samples were stored at 4°C prior to analysis. Samples were analyzed for intact hGH content using a radio immuno assay (RIA). At the end of study the rats are euthanized for gross clinical observation and the depot was retrieved for intactness observations.

[000157] Figures 11 & 12 illustrate representative *in vivo* release profiles of human growth hormone ("hGH") obtained in rats from various depot compositions, including those of the present invention. The *in vivo* release profile of the depot formulations with benzyl alcohol are comparable to the control formulations (without benzyl alcohol). Thus, the depot compositions of the present invention reduce the injection force significantly without compromising the *in vivo* release profile of the beneficial agent.

[000158] At the end of study (i.e. at day 28) the depots were retrieved from the rats. Generally, a one-piece intact round-shaped depot was recovered corresponding to each injected depot in the animal.

5

Example 14Bupivacaine *In Vivo* Studies

[000159] *In vivo* studies in rats (4 per group) were performed following an open protocol to determine plasma levels of bupivacaine upon systemic administration of bupivacaine via the implant systems of this invention. Depot gel bupivacaine formulations were loaded into customized 0.5 cc disposable syringes. Disposable 18 gauge needles were attached to the syringes and were heated to 37°C using a circulator bath. Depot gel bupivacaine formulations were injected into rats and blood was drawn at specified time intervals (1 hour, 4 hours and on days 1, 2, 5, 7, 9 and 14) and analyzed for bupivacaine using LC/MS. At the end of study (i.e., at day 14) the rats were euthanized for gross clinical observation and the depot was retrieved for intactness observations.

[000160] Figures 13, 14 & 15 illustrate representative *in vivo* release profiles of bupivacaine obtained in rats from various depot compositions, including those of the present invention. The *in vivo* release profiles of the depot formulations with benzyl alcohol are comparable to the control formulations (without benzyl alcohol). Thus, the depot compositions of the present invention reduce the injection force significantly without compromising the *in vivo* release profile of the beneficial agent.

[000161] At the end of study (i.e. at day 14) the depots were retrieved from the rats. Generally, a one-piece intact round-shaped depot was recovered corresponding to each injected depot in the animal.

Example 15Stability of hGH in the depot formulations

[000162] Depot gel hGH formulations were stored at 5°C. At
 5 predetermined time points, the depot gel hGH formulation (0.3 ml) was treated
 with a cooled organic solvent (a 50/50 mixture of methylene chloride/acetone,
 5°C, 3x3 ml) to extract the polymer and solvents from the depot formulation.
 The resulting residual hGH was dissolved in a PBS buffer (2 ml, pH 7.4) and
 the purity of the hGH was analyzed by size exclusion chromatography (SEC).
 10 Figure 16 illustrates the stability of hGH in the various depot gel hGH
 formulations, including those of the present invention, as a function of time at 5
 °C. The stability of hGH in the depot formulations comprising benzyl alcohol is
 comparable to the control formulations without benzyl alcohol. Thus, the depot
 formulations of the present invention reduce the injection force significantly
 15 without compromising the stability of the beneficial agent, e.g. hGH.

Example 16Parameters affecting the injection force

20 [000163] The following parameters affect the injection force for a given
 formulation at pre-set temperature: the radius of syringe (r); inner radius of
 needle (R); needle length (L); injection speed (Q). The effect of these four
 parameters on the injection force was determined using a fractional factorial
 design approach (8 trials) with one near center point for confirmation. The
 25 details of the design are summarized in Table 6 (trials 1-9). The injection force
 was tested using the following formulation (n = 3): the vehicle containing PLGA
 RG502/BB/BA (40/45/15 wt%), loaded with lysozyme particles (10 wt% 30
 µm). The correlation between the injection force and testing parameters was
 established using JMP software (which is very similar to the Power Law
 30 prediction) as follows:

$$F = 0.028 \cdot \frac{r^{2.475} \cdot L^{0.770} \cdot Q^{0.716}}{R^{2.630}}$$

Table 6

Trial	Needle ID ^a (mm)	Needle length ^b (mm)	Syringe ID ^c (mm)	Injection speed (mL/min)	Injection Force (N)	
					Avg	SD
1	0.191	12.7	2.3	0.05	14.6	0.8
2	0.292	50.8	3.25	0.5	172.2	5.3
3	0.292	12.7	3.25	0.05	8.6	0.2
4	0.191	12.7	3.25	0.5	176.0	2.6
5	0.292	50.8	2.3	0.05	13.4	0.3
6	0.292	12.7	2.3	0.5	30.0	2.5
7	0.191	50.8	3.25	0.05	127.0	2.3
8	0.191	50.8	2.3	0.5	161.4	4.5
9	0.241	25.4	2.3	0.25	48.8	0.5

^a Needles having following gauges were used: 24G (ID = 0.292 mm), 25G (ID = 0.241 mm) and 27G (ID = 0.191 mm);

^b Needle having following lengths were used: 0.5 inch (12.7 mm), 1 inch (25.4 mm), 2 inches (50.8 mm);

^c Two different syringes (Hamilton): 250 μ L (ID = 2.30 mm); 500 μ L (ID = 3.25 mm).

Example 17

Effect of drug particle size and loading on the injection force of depot formulations

[000164] Particle size and amount of loading of the beneficial agent, i.e. drug, are additional factors potentially affecting the injection force of the depot formulation. Depot gel lysozyme formulations were used to determine the effect of drug particle size and loading on the injection force of the depot formulations. Various depot gel lysozyme formulations of present invention containing differing amounts (5-30% loading) and particle sizes (5-50 μ m) of lysozyme were tested for injection force using 27 gauge, 2" needles. The injection speed was set at 50 μ L/min. The formulations tested are summarized in Table 7. As illustrated in Figure 17, the injection force of the depot formulations increases with the increase of drug particle loading. With 10 wt% particle loading, the injection forces increase about 50% compared to the corresponding gel formulation, regardless of the composition of the gel formulation. The injection force appears to be proportional to the amount of benzyl alcohol in the gel formulation, further indicating that benzyl alcohol

significantly reduces the injection force of the depot gel formulations of the invention.

Table 7

Formulation	PLGA RG 502 (wt%)	Benzyl Benzoate (BB, wt%)	Benzyl Alcohol (BA, wt%)	Particle loading (wt%)	Particle size (μ m)
25	38.0	42.8	14.2	5	5
26	34.0	38.3	12.8	15	5
27	38.0	42.8	14.2	5	50
28	34.0	38.3	12.8	15	50
29	36.0	40.5	13.5	10	20
30	38.0	-	57.0	5	5
31	34.0	-	51.0	15	5
32	38.0	-	57.0	5	50
33	34.0	-	51.0	15	50
34	36.0	-	54.0	10	20
35	30.8	34.7	11.6	23	50
36	28.0	31.5	10.5	30	50
37	30.8	-	46.2	23	50
38	28.0	-	42.0	30	50
39	40.0	45.0	15.0	0	-
40	40.0	-	60.0	0	-

5

Example 18

PDGF Preformulation Preparation

[000165] Various Platelet Derived Growth Factor (PDGF) preformulations
10 were prepared as follows:

Dialysis

[000166] The following buffers were prepared for the dialysis:

(A) The histidine buffer (10 mM, pH 6, 2 L) was prepared as follows. L-
15 histidine (3.10g) was weighed in a volumetric flask (2 L). Milli-Q water
(1800ml) was added to the flask and the mixture was stirred until the solid
dissolved. HCl (0.1N, 8 ml) was added, the pH was checked and adjusted to
6. The solution was diluted with milli-Q water to a volume of 2L.

(B) The succinate buffer (10mM, pH 6, 2 L) was prepared as follows. Succinic
20 acid (5.91g) was weighed in a volumetric flask (250ml) and milli-Q water

(250ml) was added to obtain succinic acid solution (0.2M). NaOH solution (4g, 50% w/w) was measured in a volumetric flask (250ml) and diluted with milli-Q water to obtain NaOH solution (0.2M). The succinic acid solution (0.2M, 100ml) was mixed with the NaOH solution (0.2M, 165ml) and milli-Q water (1600ml) in a volumetric flask (2L) the pH was checked and adjusted to 6. The solution was diluted with milli-Q water to a volume of 2L.

[000167] The PDGF-BB bulk solution, i.e. aqueous solution of PDGF in acetate buffer, was thawed to room temperature. Various aliquots of the PDGF-BB solution were diluted appropriately for a UV absorbance measurement, using a 1 cm path length cuvette from 400 to 250 nm. The absorbance was recorded at 280 nm and corrected for light scattering in the 400 to 330 nm range using a log(Absorbance) vs. log(wavelength) extrapolation. The concentration of PDGF-BB was determined using an extinction coefficient of 0.574 ml/mg x cm. The PDGF-BB solution was concentrated using a Millipore Tangential Flow Filtration System (having a reservoir (100 ml) and a Pellicon XL PLCCC 5000 MWCO regenerated cellulose membrane), and the protein was divided into two parts. One half of the protein was diafiltered against the histidine buffer (10mM, pH 6); and the second half of the protein was diafiltered against the succinate buffer (10mM, pH 6), according to manufacturer's instructions. After diafiltration, an aliquot from each part was appropriately diluted for an absorbance measurement as described above, and analyzed by reverse phase and size exclusion high pressure liquid chromatography (HPLC). The protein solution was removed from the TFF system according to Millipore TFF instructions.

PDGF-BB pre-formulation

[000168] Various pre-formulations of PDGF-BB were prepared by adding different excipients, e.g. sucrose, tween 20, Zn acetate or combinations thereof, into the above diafiltrated PDGF-BB solution; the solution was buffered either with histidine or succinate to obtain the final PDGF-BB concentration in the solution of approximately 5 mg/ml (as tabulated in Tables

8 and 9). Those solutions were lyophilized under the conditions described below to achieve the dry PDGF-BB formulations.

Lyophilization

5

[000169] The lyophilization freezing cycle was started with an equilibration of shelf temperature at 4°C at 2.5°C/min and held at this temperature for 30 minutes. The temperature was then brought down to -50°C at 2.5°C/min and held for 3 hours. For the primary drying cycle, vacuum was applied and the shelf temperature was increased as follows: (i) -20°C at 0.14°C/min for 24 hours; (ii) -15°C at 0.14°C/min for 24 hours; and (iii) 0°C at 0.14°C/min for 12 hours. For the secondary drying cycle involves the shelf temperature was increased as follows: (i) 20°C at 0.14°C/min for 12 hours; and (ii) 30°C at 0.14°C/min for 4 hours. After drying, shelf temperature was decreased to 0°C or 4°C and held at that temperature until removal from the instrument. The vials were capped using shelf stoppering the run was stopped and the vials were removed.

10
15

Example 19

20

Preliminary stability of PDGF preformulations in the gel vehicle

[000170] All lyophilized protein formulation as listed in Tables 8 and 9, were mixed into a gel vehicle with the composition of PLGA RG502/Benzyl Benzoate (BB)/ benzyl alcohol (BA) of 40/45/15 with the loading of the protein formulation about 10 wt%. After stored at 5 °C for 1 day, the mixtures were extracted with a organic solvent mixture of methylene chloride and acetone (ratio of 50/50) as described in the example 15 above. The purity of the PDGF-BB was analyzed by both reverse phase HPLC (rpHPLC) and size exclusion chromatography (SEC). The stability data of the PDGF-BB formulation after mixing with the gel vehicle are summarized in Tables 8 and 9. In general, no distinguishable degradation of the PDGF-BB was found in the PDGF-BB formulation incorporated with the excipients as described in the example 18 and mixed with the gel vehicle of the present invention.

25
30

35

Table 8

Formulation	SA-1	SA-2	SA-3	SA-4	SA-5	Bulk PDGF
PDGF (mg)	1	1	1	1	1	
Sucrose (mg)	1	1	0	0	0	
Tween 20 (mg)	0	0.2	0.2	0	0	
Succinate (mg)	0.24	0.24	0.24	0.24	0.24	
Zn acetate (mg)	0	0	0	0	0.02	
Gel vehicle (mg) ^a	20.16	21.96	12.96	11.16	11.34	
% PDGF monomer by SEC	98.90	98.82	98.02	98.51	98.59	99.27
% PDGF dimer by SEC	1.10	1.18	1.98	1.49	1.41	0.73
% peak at RRT = 0.93 by rp-HPLC	11.5	11.1	10.7	12.7	11.0	11.1
% peak at RRT = 1.00 by rp-HPLC	87.3	87.6	87.6	86.2	87.8	87.7
% peak at RRT = 1.10 by rp-HPLC	1.1	1.2	1.1	1.1	1.1	1.2
% other peaks by rp-HPLC	0.0	0.1	0.6	0.0	0.0	0.0

a = PLGA RG502/BB/BA - 40/45/15

5

Table 9

Formulation	HA-1	HA-2	HA-3	HA-4	HA-5	Bulk PDGF
PDGF (mg)	1	1	1	1	1	
Sucrose (mg)	1	1	0	0	0	
Tween 20 (mg)	0	0.2	0.2	0	0	
Histidine (mg)	0.31	0.31	0.31	0.31	0.31	
Zn acetate (mg)	0	0	0	0	0.02	
Gel vehicle (mg) ^a	20.79	22.59	13.59	11.79	11.97	
% PDGF monomer by SEC	99.15	99.15	99.07	99.01	99.04	99.27
% PDGF dimer by SEC	0.85	0.85	0.93	0.99	0.96	0.73
% peak at RRT = 0.93 by rp-HPLC	11.3	11.0	10.9	10.8	10.9	11.1
% peak at RRT = 1.00 by rp-HPLC	87.6	87.8	87.7	88.0	88.0	87.7
% peak at RRT = 1.10 by rp-HPLC	1.1	1.1	1.2	1.2	1.1	1.2
% other peaks by rp-HPLC	0.0	0.0	0.2	0.0	0.0	0.0

a = PLGA RG502/BB/BA - 40/45/15

Example 20

Preparation of PDGF Particles

10

[000171] PDGF-BB formulations with sucrose in histidine buffer and without sucrose in succinate buffer were prepared as similar way to the example 18 above (Table 10): Thaw PDGF-BB bulk solution. Combine the solution and measure volume in a graduate cylinder. Take an aliquot and dilute appropriately for a UV absorbance measurement. Record the

15

absorbance in a 1 cm path length cuvette from 400 to 250 nm. Record the absorbance at 280 nm and correct for light scattering in the 400 to 330 nm range using a log(Absorbance) vs. log(wavelength) extrapolation. Determine the concentration of PDGF-BB using an extinction coefficient of **0.574**

- 5 ml/mgxcn. Using a Millipore Tangential Flow Filtration System with 100 ml reservoir and a Pellicon XL PLCCC 5000 MWCO regenerated cellulose membrane, concentrate if necessary, and diafilter half of the protein against 10mM histidine pH 6 and concentrate, if necessary, and diafilter the other half against 10mM succinate pH 6, according to TFF instructions. After
- 10 diafiltration, remove an aliquot from each and dilute appropriately for a UV absorbance measurement and analyze by reverse phase and size exclusion HPLC. Remove all of the protein solution from the TFF system according to Millipore TFF instructions. For PDGF-BB in 10mM histidine add sucrose to give a 1:1 final ratio with the protein (PDGF-BB at a final concentration of ~5
- 15 mg/ml). For the PDGF-BB in 10mM succinate pH 6 dilute with 10mM succinate to give a final protein concentration of approximately 5 mg/ml. Aliquot formulations were placed into glass lyophilization vials and were lyophilized under the conditions described in the Example 18 to achieve the lyophilized dry PDGF-BB formulations. Lyophilized PDGF formulations were
- 20 ground in an agate mortar and pestle. The grounded particles were sieved through a US #230 Mesh Screen (63 μ m) and are collected on a US #500 Mesh Screen (25 μ m).

Table 10

Formulation	PDGF-BB (wt%)	Succinate (wt%)	Histidine (wt%)	Sucrose (wt%)
41	81	19	-	
42	43	-	14	43

Example 21

Preparation of PDGF depot formulations

30

[000172] The PDGF depot formulations were prepared in two steps. The first step was to make the gel formulations using the procedure as described below. Appropriate amounts of pre-irradiated PLGA RG 502 and solvent were

dispensed into the Keyence hybrid mixer bowl (made from high density polyethylene (HDPE)). The mixing bowl was tightly sealed, placed into the hybrid mixer (Model HM-501, Keyence Corp., Japan) and mixed (5-10 minutes) at the mixing speed (revolution 2000 rpm, rotation 800 rpm).

5

[000173] Mixing of particles in the gel was performed at room temperature in a glass syringe (10 ml or 25 ml). The PDGF particles and gel were first weighed and transferred into the syringe. Then, the PDGF particles and gel mixture were thoroughly blended by conventional mixing using a Caframo
10 mechanical stirrer with an attached square-tip metal spatula. Resulting formulations are tabulated in Table 11.

Table 11

Formulation	Polymer (%) (PLGA RG-502, MW = 16,000)	Benzyl Benzoate (%)	Benzyl Alcohol (%)
43 ^a	31.5	43.9	14.6
44 ^b	31.5	43.9	14.6
45 ^a	31.5	29.3	29.2
46 ^b	31.5	29.3	29.2

15

a = 10% formulation 41;
b = 10% formulation 42.

20

Example 22

Stability of PDGF in the depot formulations

[000174] Depot gel PDGF formulations were stored for different periods of time at 5, 25 and 40 °C, respectively. At predetermined time points, the depot
25 gel PDGF-BB formulation (0.3 ml) was treated with a cooled organic solvent (a 50/50 mixture of methylene chloride/acetone, at 5°C, 3x3.0 ml). The resulting residual PDGF-BB was dissolved in a PBS buffer (2 ml, pH 7.4) and the purity of the PDGF was analyzed by both reverse phase HPLC (rpHPLC) and size exclusion chromatography (SEC) HPLC. Figures 18-20 illustrate the stability
30 of PDGF (% monomer by SEC) in the various depot formulations, including those of the present invention, as a function of time at 5 °C (Figure 18), 25 °C

(Figure 19) and 40 °C (Figure 20), respectively. Table 12 summarizes the chemical stability of PDGF tested by rpHPLC in the various depot formulations, including those of the present invention, as a function of time at 5 °C, 25 °C and 40 °C, respectively. As illustrated in Figures 18-20 and Table 12, depot gel PDGF formulations containing sucrose demonstrated surprisingly good stability with minimal loss of monomer content and chemical degradation, as compared to the depot gel PDGF formulations without sucrose, at all temperatures measured. Sucrose has a significant stabilizing effect on the various depot formulations of the present invention.

10

Table 12

Formulation	Temp.	Time (day)	RP-HPLC (% Peak Area)			
			Peak at (RRT=0.93)	Peak at (RRT=1.00)	Peak at (RRT=1.09)	Other Peak(s)
Bulk PDGF		0	11.1	87.7	1.2	0
43		0	13.03 ± 0.12	85.04 ± 0.43	1.2 ± 0.35	0.72 ± 0.09
	5°C	14	12.77 ± 0.28	85.94 ± 0.17	1.06 ± 0.03	0.23 ± 0.19
	5°C	28	12.17 ± 0.32	86.03 ± 0.77	1.11 ± 0.34	0.69 ± 0.08
	5°C	90	12.14 ± 0.35	86.14 ± 0.42	0.78 ± 0.01	0.94 ± 0.08
	25°C	14	9.57 ± 0.14	89.52 ± 0.18	(shoulder)	0.91 ± 0.03
	25°C	28	8.24 ± 0.12	90.98 ± 0.09	(shoulder)	0.78 ± 0.04
	25°C	90	8.96 ± 0.21	90.16 ± 0.23	(N/A)	0.88 ± 0.01
	40°C	14	7.22 ± 0.06	91.96 ± 0.09	(shoulder)	0.83 ± 0.02
	40°C	28	5.54 ± 0.13	93.80 ± 0.09	(shoulder)	0.66 ± 0.09
44		0	13.25 ± 0.16	84.97 ± 0.34	1.5 ± 0.36	0.28 ± 0.86
	5°C	14	13.07 ± 0.04	85.32 ± 0.34	1.43 ± 0.36	0.18 ± 0.03
	5°C	28	12.93 ± 0.08	85.62 ± 0.43	1.27 ± 0.37	0.18 ± 0.06
	5°C	90	14.07 ± 0.25	83.87 ± 0.41	1.39 ± 0.44	0.67 ± 0.28
	25°C	14	12.19 ± 0.10	86.28 ± 0.52	1.25 ± 0.33	0.28 ± 0.13
	25°C	28	11.79 ± 0.27	86.82 ± 0.09	1.30 ± 0.35	0.10 ± 0.02
	25°C	90	14.57 ± 0.11	83.84 ± 0.57	1.43 ± 0.46	0.17 ± 0.00
	40°C	14	12.93 ± 0.08	85.65 ± 0.26	1.26 ± 0.39	0.16 ± 0.07
	40°C	28	13.09 ± 0.24	85.18 ± 0.17	1.59 ± 0.43	0.15 ± 0.04
45		0	12.39 ± 0.28	85.91 ± 0.26	0.96 ± 0.02	0.73 ± 0.04
	5°C	14	12.21 ± 0.29	86.05 ± 0.34	1.10 ± 0.32	0.64 ± 0.36
	5°C	28	11.38 ± 0.18	87.11 ± 0.70	0.81 ± 0.04	0.97 ± 0.08
	25°C	14	8.50 ± 0.19	90.40 ± 0.27	(shoulder)	1.10 ± 0.08
	25°C	28	7.73 ± 0.19	91.25 ± 0.18	(shoulder)	1.02 ± 0.04
	25°C	90	7.48 ± 0.64	91.67 ± 0.66	(N/A)	0.86 ± 0.01
	40°C	14	(shoulder)	99.17 ± 0.00	(shoulder)	0.83 ± 0.04
	40°C	28	(shoulder)	99.56 ± 0.00	(shoulder)	0.44 ± 0.03
46		0	12.71 ± 0.14	85.90 ± 0.26	1.1 ± 0.01	0.3 ± 0.03
	5°C	14	13.04 ± 0.25	85.10 ± 0.60	1.45 ± 0.37	0.41 ± 0.13
	5°C	28	12.67 ± 0.20	86.05 ± 0.17	1.04 ± 0.02	0.24 ± 0.05
	5°C	90	14.65 ± 0.08	83.65 ± 0.07	1.04 ± 0.01	0.66 ± 0.13
	25°C	14	12.94 ± 0.06	85.27 ± 0.43	1.50 ± 0.33	0.29 ± 0.10
	25°C	28	12.64 ± 0.19	85.55 ± 0.34	1.51 ± 0.41	0.30 ± 0.09
	25°C	90	14.11 ± 0.15	84.68 ± 0.10	1.01 ± 0.01	0.21 ± 0.04
	40°C	14	12.10 ± 0.18	85.76 ± 0.34	1.26 ± 0.39	0.87 ± 0.46
	40°C	28	11.12 ± 0.22	88.05 ± 0.88	(shoulder)	0.19 ± 0.03

Example 23In vitro release of PDGF from the depot formulations

[000175] The in vitro release of PDGF from the depot gel PDGF
5 formulation of the present invention was performed as follows. The depot gel
PDGF formulation (80-120 mg) was loaded into a tea bag and placed in a 20
mL scintillation vial and the release medium (5 mL, phosphate buffer saline
(PBS) + 0.1% Tween 20, pH 7.4) was added to the vial. The vial was
10 incubated in a 37 °C water bath with gentle agitation. The medium was
replaced daily for the first 5 days, then twice a week thereafter till the end of
release duration. The amount of PDGF released from the depot was
measured by size exclusion chromatography (SEC) HPLC. As illustrated in
Figure 21, sustained release of PDGF from the depot formulations of the
present invention was obtained for over a month.

15

Example 24Effect of catheter length on the injection force

[000176] To evaluate the effect of catheter length on the injection forces of
20 the depot formulation of present invention, polyimide catheters (0.16" ID 72")
were cut into different lengths and the injection force of formulation 40 in Table
7 was tested. Three different injection speeds were used. As illustrated in
Figure 22, the injection force increases linearly with the length of the catheter.
The higher the injection speed the higher the injection forces.

25

Example 25Injection force of depot formulations

[000177] Various formulations of the present invention were tested for the
30 injection force through either needles (27 gauge, 2") at different injection
speeds (50 and 100 µl/min) or Nitinol catheters (25 gauge, 72") at a fixed
injection speed (50 µl/min). The formulations and injection force data are
summarized in Table 9. As can be seen from Table 9, the injection forces of
the formulation with higher amount of benzyl alcohol in the formulation are
35 generally lower than those with less amount of benzyl alcohol. Furthermore,

the depot formulations with drug particle loaded generally exhibit higher injection forces than the respective gel formulations.

Table 13

5

Formulation	PLGA RG 502 (wt%)	Benzyl Benzoate (wt%)	Benzyl Alcohol (wt%)	Injection force (N)		
				Syringe (500 μ l) with needle (27 gauge, 2")		Syringe (250 μ l) with catheter (25 gauge, 72")
				50 μ l/min ^c	100 μ l/min ^c	50 μ l/min ^a
34 ^a	31.5	0	58.5	-	45.4 \pm 6.7	23.1 \pm 1.3
35 ^b	35	0	65	18.2 \pm 3.1	30.2 \pm 4.4	35.6 \pm 2.2
36 ^a	31.5	43.9	14.6	-	88.1 \pm 3.6	60.9 \pm 5.8
37 ^b	35	48.8	16.2	36.9 \pm 1.3	66.7 \pm 0.4	26.7 \pm 0.4
38 ^a	36	27	27	-	109.4 \pm 1.3	69.3 \pm 5.3
39 ^b	40	30	30	48.5 \pm 1.3	96.3 \pm 1.3	28.9 \pm 0.4
40 ^a	36	40.5	13.5	-	184.1 \pm 3.6	114.3 \pm 4.9
41 ^b	40	45	15	84.1 \pm 0.4	146.3 \pm 1.3	54.7 \pm 2.7

a = 10% 50 μ m lysozyme particles loaded;

b = gel formulations only;

c = injection speed (\square l/min).

- 10 [000178] The above-described exemplary embodiments are intended to be illustrative in all respects, rather than restrictive, of the present invention. Thus the present invention is capable of many variations in detailed implementation that can be derived from the description contained herein by a person skilled in the art. All such variations and modifications are considered
- 15 to be within the scope and spirit of the present invention.

We Claim:

1. A catheter injectable depot composition comprising:
 - (a) a bioerodible, biocompatible polymer;
 - 5 (b) a solvent having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein said solvent is an aromatic alcohol;
 - (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being
10 selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
 - (d) a beneficial agent.
- 15 2. A catheter injectable depot composition comprising:
 - (a) a bioerodible, biocompatible polymer;
 - (b) a solvent selected from the group consisting of aromatic alcohols, esters of aromatic acids, aromatic ketones, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in
20 an amount effective to plasticize the polymer and form a gel therewith;
 - (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the
25 solvent and the thixotropic agent; and
 - (d) a beneficial agent.
3. The catheter injectable depot composition of claim 1 or claim 2, wherein the aromatic alcohol has the structural formula (I)

30



wherein Ar is aryl or heteroaryl, n is zero or 1, and L is a linking moiety.

4. The catheter injectable depot composition of claim 3, wherein Ar is monocyclic aryl or heteroaryl, n is 1, and L is lower alkylene optionally containing at least one heteroatom.
- 5
5. The catheter injectable depot composition of claim 4, wherein Ar is monocyclic aryl and L is lower alkylene.
6. The catheter injectable depot composition of claim 5, wherein Ar is
- 10 phenyl and L is methylene.
7. The catheter injectable depot composition of claim 2, wherein the solvent is mixture of an aromatic alcohol and an ester of an aromatic acid.
- 15 8. The catheter injectable depot composition of claim 7, wherein the aromatic alcohol is benzyl alcohol and the ester of an aromatic acid is a lower alkyl ester or an aralkyl ester of benzoic acid.
9. The catheter injectable depot composition of claim 8, wherein the ester
- 20 of an aromatic acid is benzyl benzoate and the lower alkyl ester of an aromatic acid is ethyl benzoate.
10. The catheter injectable depot composition of claim 1 or claim 2, wherein the polymer is selected from the group consisting of polylactides,
- 25 polyglycolides, polycaprolactones, polyanhydrides, polyamines, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyphosphoesters, polyorthocarbonates, polyphosphazenes, succinates, poly(malic acid), poly(amino acids), polyvinylpyrrolidone, polyethylene glycol,
- 30 polyhydroxycellulose, chitin, chitosan, hyaluronic acid, and copolymers, terpolymers and mixtures thereof.

11. The catheter injectable depot composition of claim 1 or claim 2, wherein the polymer is a lactic acid-based polymer.
12. The catheter injectable depot composition of claim 11, wherein the polymer is a copolymer of at least two of the following monomers: lactic acid, glycolic acid and caprolactone.
13. A catheter injectable depot composition comprising:
- (a) approximately 5 wt.% to approximately 90 wt.% of a bioerodible, biocompatible polymer;
- (b) an aromatic alcohol having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)
- $$\text{Ar-(L)}_n\text{-OH} \quad (I)$$
- in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety;
- (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- (d) a beneficial agent.
14. A catheter injectable depot composition comprising:
- (a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;
- (b) an aromatic alcohol having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)
- $$\text{Ar-(L)}_n\text{-OH} \quad (I)$$
- in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety;

- (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- (d) a beneficial agent.

15. A catheter injectable depot composition comprising:
- (a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;
- (b) a solvent selected from the group consisting of an aromatic alcohol, an ester of an aromatic acid, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety;

- (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- (d) a beneficial agent.

16. The catheter injectable depot composition of any one of claims 13, 14, or 15, wherein the polymer represents approximately 10 wt.% to approximately 85 wt.% of the composition.

17. The catheter injectable depot composition of claim 17, wherein the polymer represents approximately 20 wt.% to approximately 75 wt.% of the composition.

18. The catheter injectable depot composition of claim 13, wherein the polymer is selected from the group consisting of polylactides, polyglycolides, polycaprolactones, polyanhydrides, polyamines, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyphosphoesters, polyorthocarbonates, polyphosphazenes, succinates, poly(malic acid), poly(amino acids), polyvinylpyrrolidone, polyethylene glycol, polyhydroxycellulose, chitin, chitosan, hyaluronic acid, and copolymers, terpolymers and mixtures thereof.
- 10 19. The catheter injectable depot composition of any one of claims 13, 14 or 15, wherein the polymer is a copolymer of lactic acid and glycolic acid.
- 15 20. The catheter injectable depot composition of claim 19, wherein the polymer is a copolymer of at least two of the following monomers: lactic acid, glycolic acid and caprolactone.
- 20 21. The catheter injectable depot composition of any one of claims 13, 14 or 15, wherein Ar is monocyclic aryl or heteroaryl, n is 1, and L is lower alkylene optionally containing at least one heteroatom.
22. The catheter injectable depot composition of claim 21, wherein Ar is monocyclic aryl and L is lower alkylene.
- 25 23. The catheter injectable depot composition of claim 22, wherein Ar is phenyl and L is methylene.
24. The catheter injectable depot composition of any one of claims 13, 14 or 15, wherein the aromatic alcohol is benzyl alcohol.
- 30 25. The catheter injectable depot composition of claim 15, wherein the solvent is mixture of an aromatic alcohol and an ester of an aromatic acid.

26. The catheter injectable depot composition of claim 25, wherein the aromatic alcohol is benzyl alcohol and the ester of an aromatic acid is a lower alkyl ester or an aralkyl ester of benzoic acid.
- 5 27. The catheter injectable depot composition of claim 26, wherein the ester of an aromatic acid is benzyl benzoate and the lower alkyl ester of an aromatic acid is ethyl benzoate.
28. The catheter injectable depot composition of claim 27, wherein the ratio
10 of the aromatic alcohol to the ester of an aromatic acid is in the range of about 1% to about 99% by weight.
29. The catheter injectable depot composition of claim 28, wherein the ratio
15 of the aromatic alcohol to the ester of an aromatic acid is in the range of about 20% to about 80% by weight.
30. A catheter injectable depot composition comprising:
(a) approximately 5 wt.% to approximately 90 wt.% a poly(lactide-co-glycolide) (PLGA) copolymer having a weight average molecular weight in the
20 range of approximately 1,000 to approximately 120,000;
(b) approximately 5 wt.% to approximately 90 wt.% an aromatic alcohol solvent having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith;
(c) a thixotropic amount of thixotropic agent mixed with the polymer
25 solution effective to form a thixotropic composition, wherein the thixotropic agent is ethanol and the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
(d) a beneficial agent.
- 30 31. The catheter injectable depot composition of claim 30, wherein the aromatic alcohol is benzyl alcohol.

32. A catheter injectable depot composition comprising:
- (a) approximately 5 wt.% to approximately 90 wt.% of a poly(lactide-co-glycolide), (PLGA) copolymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;
- 5 (b) approximately 5 wt.% to approximately 90 wt.% of a solvent selected from the group consisting of an aromatic alcohol, an ester of an aromatic acid, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith,
- 10 (c) a thixotropic amount of thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, wherein the thixotropic agent is ethanol and the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- 15 (d) a beneficial agent.
33. The catheter injectable depot composition of claim 32, wherein the aromatic alcohol is benzyl alcohol and the ester of an aromatic acid is benzyl benzoate.
- 20 34. A catheter injectable depot composition comprising:
- a bioerodible, biocompatible polymer;
- an aromatic alcohol having miscibility in water of less than or equal to 7 wt.% at 25°C, in an amount effective to plasticize the polymer and form a gel
- 25 therewith; and
- a beneficial agent,
- wherein the composition is free of monohydric lower alkanols.
35. A catheter injectable depot composition comprising:
- 30 a bioerodible, biocompatible polymer;
- a solvent selected from the group consisting of esters of aromatic acids, aromatic ketones, and mixtures thereof, said solvent having miscibility

in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith;

an effective thixotropic amount of an aromatic alcohol having miscibility in water of less than or equal to 7%; and

5 a beneficial agent,


wherein the composition is free of monohydric lower alkanols.

36. A catheter injectable depot composition comprising:

(a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular
10 weight in the range of approximately 1,000 to approximately 120,000;

(b) an aromatic alcohol having miscibility in water of less than or equal to 5% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)

15



in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety; and

(c) a beneficial agent,

20

wherein the composition is free of monohydric lower alkanols.

37. The catheter injectable depot composition of claim 36, wherein Ar is monocyclic aryl or heteroaryl, n is 1, and L is lower alkylene optionally containing at least one heteroatom.

25

38. The catheter injectable depot composition of claim 37, wherein Ar is monocyclic aryl and L is lower alkylene.

30

39. The catheter injectable depot composition of claim 38, wherein Ar is phenyl and L is methylene.

40. The catheter injectable depot composition of claim 34 or claim 35, wherein the polymer is selected from the group consisting of polylactides,

polyglycolides, polycaprolactones, polyanhydrides, polyamines, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyphosphoesters, polyorthocarbonates, polyphosphazenes, succinates, poly(malic acid),
5 poly(amino acids), polyvinylpyrrolidone, polyethylene glycol, polyhydroxycellulose, chitin, chitosan, hyaluronic acid, and copolymers, terpolymers and mixtures thereof.

10 41. The catheter injectable depot composition of claim 34 or claim 35, wherein the polymer is a lactic acid-based polymer.

42. The catheter injectable depot composition of any one of claims 34, 35 or 36, wherein the polymer is a copolymer of at least two of the following monomers: lactic acid, glycolic acid and caprolactone.

15 43. The catheter injectable depot composition of any one of claims 34, 35 or 36, further including at least one of the following: a pore former; a solubility modulator for the beneficial agent; and an osmotic agent.

20 44. The catheter injectable depot composition of any one of claims 34, 35 or 36, wherein the composition is free of solvents having miscibility in water that is greater than 7 wt.% at 25°C.

25 45. The catheter injectable depot composition of claim 42, wherein the polymer represents approximately 10 wt.% to approximately 85 wt.% of the composition.

30 46. The catheter injectable depot composition of claim 45, wherein the polymer represents approximately 20 wt.% to approximately 75 wt.% of the composition.

47. The catheter injectable depot composition of claim 42, wherein the aromatic alcohol is benzyl alcohol and the ester of an aromatic acid is a lower alkyl ester or an aralkyl ester of benzoic acid.
- 5 48. The catheter injectable depot composition of claim 47, wherein the ester of an aromatic acid is benzyl benzoate and the lower alkyl ester of an aromatic acid is ethyl benzoate.
49. The catheter injectable depot composition of claim 47, wherein the ratio
10 of the aromatic alcohol to the ester of an aromatic acid is in the range of about 1% to about 99% by weight.
50. The catheter injectable depot composition of claim 49, wherein the ratio
15 of the aromatic alcohol to the ester of an aromatic acid is in the range of about 20% to about 80% by weight.
51. A catheter injectable depot composition comprising:
(a) approximately 5 wt.% to approximately 90 wt.% a poly(lactide-co-glycolide) (PLGA) copolymer having a weight average molecular weight in the
20 range of approximately 1,000 to approximately 120,000;
(b) approximately 5 wt.% to approximately 90 wt.% an aromatic alcohol solvent having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith; and
(c) a beneficial agent;
25 wherein the composition is free of monohydric lower alkanols
52. The catheter injectable depot composition of claim 51, wherein the aromatic alcohol is benzyl alcohol.
- 30 53. A catheter injectable depot composition comprising:
(a) approximately 5 wt.% to approximately 90 wt.% of a poly(lactide-co-glycolide) (PLGA) copolymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;

- (b) approximately 5 wt.% to approximately 90 wt.% of a solvent selected from the group consisting of an aromatic alcohol, an ester of an aromatic acid, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith; and
- (c) a beneficial agent;
- wherein the composition is free of monohydric lower alkanols.

54. The catheter injectable depot composition of claim 53, wherein the aromatic alcohol is benzyl alcohol and the ester of an aromatic acid is benzyl benzoate.

55. The catheter injectable depot composition of any of the preceding claims wherein the thixotropic agent is ethanol.

56. The catheter injectable depot composition of claim 55 wherein the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the thixotropic agent.

57. The catheter injectable depot composition of claim 55 wherein the amount of ethanol is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the thixotropic agent.

58. The catheter injectable depot composition of claim 55 wherein the amount of ethanol is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the thixotropic agent.

59. The catheter injectable depot composition of any of the preceding claims, further including at least one of the following: a pore former; a solubility modulator for the beneficial agent; and an osmotic agent.

60. The catheter injectable depot composition of any of the preceding claims wherein the beneficial agent is selected from a drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-inflammatory agents, antiproliferative agents, antimetabolic agents, angiogenic agents, anticoagulants, fibrinolytic agents, growth factors, antibodies, ocular drugs, and metabolites, analogs, derivatives, and fragments thereof.
61. The catheter injectable depot composition of claim 60 wherein the beneficial agent is a growth hormone.
62. The catheter injectable depot composition of claim 60 wherein the beneficial agent is a growth factor.
63. The catheter injectable depot composition of claim 62 wherein the growth factor is selected from epidermal growth factors (EGFs), platelet-derived growth factor (PDGFs), insulin-like growth factors (IGFs), fibroblast-growth factors (FGFs), transforming-growth factors (TGFs), interleukins (ILs), colony-stimulating factors (CSFs, MCFs, GCSFs, GMCSFs), Interferons (IFNs), endothelial growth factors (VEGF, EGFs), erythropoietins (EPOs), angiopoietins (ANGs), placenta-derived growth factors (PIGFs), and hypoxia induced transcriptional regulators (HIFs).
64. The catheter injectable depot composition of claim 60 wherein the beneficial agent is present in an amount of from 0.1 to 50% by weight of the combined amounts of the polymer, the solvent and the beneficial agent.
65. The catheter injectable depot composition of claim 60 wherein the beneficial agent is in the form of particles dispersed or dissolved in the viscous gel.

66. The catheter injectable depot composition of claim 65 wherein the beneficial agent is in the form of particles having an average particle size of from 0.1 to 250 microns.
- 5 67. The catheter injectable depot composition of claim 65 wherein the beneficial agent is in the form of particles wherein the particle further comprises a component selected from the group consisting of a stabilizing agent, bulking agent, chelating agent and a buffering agent.
- 10 68. A method of administering a beneficial agent to a subject comprising the steps of:
- (1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:
 - (a) a bioerodible, biocompatible polymer;
 - 15 (b) a solvent having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein said solvent is an aromatic alcohol;
 - (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic
 - 20 agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
 - (d) a beneficial agent;
 - (2) delivering the depot composition to said subject at a site within the
 - 25 subject; and
 - (3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.
69. A method of administering a beneficial agent to a subject comprising
- 30 the steps of:
- (1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:
 - (a) a bioerodible, biocompatible polymer;

(b) a solvent selected from the group consisting of aromatic alcohols, esters of aromatic acids, aromatic ketones, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith;

(c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and

(d) a beneficial agent;

(2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

70. A method of administering a beneficial agent to a subject comprising the steps of:

(1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

(a) approximately 5 wt.% to approximately 90 wt.% of a bioerodible, biocompatible polymer;

(b) an aromatic alcohol having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety;

(c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and

- (d) a beneficial agent;
 - (2) delivering the depot composition to said subject at a site within the subject; and
 - (3) forming an implant at the site wherein the implant provides
- 5 sustained release of the beneficial agent at the site.

71. A method of administering a beneficial agent to a subject comprising the steps of:

- (1) providing a catheter having an injectable depot composition, said
- 10 catheter injectable depot composition comprising:

- (a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;

- 15 (b) an aromatic alcohol having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



- 20 in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety;

- (c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of
- 25 the solvent and the thixotropic agent; and

- (d) a beneficial agent;
- (2) delivering the depot composition to said subject at a site within the subject; and
- (3) forming an implant at the site wherein the implant provides
- 30 sustained release of the beneficial agent at the site.

72. A method of administering a beneficial agent to a subject comprising the steps of:

(1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

(a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;

(b) a solvent selected from the group consisting of an aromatic alcohol, an ester of an aromatic acid, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety;

(c) a thixotropic amount of a thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, the thixotropic agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the thixotropic agent; and

(d) a beneficial agent;

(2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

25

73. A method of administering a beneficial agent to a subject comprising the steps of:

(1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

(a) approximately 5 wt.% to approximately 90 wt.% a poly(lactide-co-glycolide) (PLGA) copolymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;

- (b) approximately 5 wt.% to approximately 90 wt.% an aromatic alcohol solvent having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith;
- (c) a thixotropic amount of thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, wherein the thixotropic agent is ethanol and the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- (d) a beneficial agent;
- (2) delivering the depot composition to said subject at a site within the subject; and
- (3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.
74. A method of administering a beneficial agent to a subject comprising the steps of:
- (1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:
- (a) approximately 5 wt.% to approximately 90 wt.% of a poly(lactide-co-glycolide) (PLGA) copolymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;
- (b) approximately 5 wt.% to approximately 90 wt.% of a solvent selected from the group consisting of an aromatic alcohol, an ester of an aromatic acid, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith,
- (c) a thixotropic amount of thixotropic agent mixed with the polymer solution effective to form a thixotropic composition, wherein the thixotropic agent is ethanol and the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the thixotropic agent; and
- (d) a beneficial agent;

(2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

5

75. A method of administering a beneficial agent to a subject comprising the steps of:

(1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

10

(a) a bioerodible, biocompatible polymer;

(b) an aromatic alcohol having miscibility in water of less than or equal to 7 wt.% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith; and

15

(c) a beneficial agent; wherein the composition is free of monohydric lower alkanols;

(2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

20

76. A method of administering a beneficial agent to a subject comprising the steps of:

(1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

25

(a) a bioerodible, biocompatible polymer;

(b) a solvent selected from the group consisting of esters of aromatic acids, aromatic ketones, and mixtures thereof, said solvent having miscibility in water of less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith;

30

(c) an effective thixotropic amount of an aromatic alcohol having miscibility in water of less than or equal to 7%; and

(d) a beneficial agent; wherein the composition is free of monohydric lower alkanols;

(2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

5

77. A method of administering a beneficial agent to a subject comprising the steps of:

(1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

10 (a) approximately 5 wt.% to approximately 90 wt.% of a biodegradable, biocompatible lactic acid-based polymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;

15 (b) an aromatic alcohol having miscibility in water of less than or equal to 5% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, wherein the aromatic alcohol has the structural formula (I)



20 in which Ar is a substituted or unsubstituted aryl or heteroaryl group, n is zero or 1, and L is a linking moiety; and

(c) a beneficial agent; wherein the composition is free of monohydric lower alkanols;

25 (2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

78. A method of administering a beneficial agent to a subject comprising the steps of:

30 (1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

(a) approximately 5 wt.% to approximately 90 wt.% a poly(lactide-co-glycolide) (PLGA) copolymer having a weight average molecular weight in the range of approximately 1,000 to approximately 120,000;

5 (b) approximately 5 wt.% to approximately 90 wt.% an aromatic alcohol solvent having miscibility in water of less than or equal to 7% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith; and

(c) a beneficial agent; wherein the composition is free of monohydric lower alkanols;

10 (2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

79. A method of administering a beneficial agent to a subject comprising
15 the steps of:

(1) providing a catheter having an injectable depot composition, said catheter injectable depot composition comprising:

(a) approximately 5 wt.% to approximately 90 wt.% of a poly(lactide-co-glycolide) (PLGA) copolymer having a weight average
20 molecular weight in the range of approximately 1,000 to approximately 120,000;

(b) approximately 5 wt.% to approximately 90 wt.% of a solvent selected from the group consisting of an aromatic alcohol, an ester of an aromatic acid, and mixtures thereof, said solvent having miscibility in water of
25 less than or equal to 7% at 25°C, and present in an amount effective to plasticize the polymer and form a gel therewith; and

(c) a beneficial agent; wherein the composition is free of monohydric lower alkanols;

30 (2) delivering the depot composition to said subject at a site within the subject; and

(3) forming an implant at the site wherein the implant provides sustained release of the beneficial agent at the site.

80. The method according to any one of claims 68 to 79, wherein the catheter further comprises a needle having a diameter greater than 16 gauge.
81. The method according to claim 80, wherein the needle has a diameter
5 greater than 20 gauge.
82. The method according to Claim 81, wherein the needle has a diameter greater than 22 gauge.
- 10 83. The method according to Claim 82, wherein the needle has a diameter greater than 24 gauge.
84. The method according to Claim 80, wherein the catheter has a length of less than 8 feet.
- 15 85. The method according to claim 84 wherein the catheter has a length ranging from about 3 feet to about 6 feet.
86. The method according to Claim 84, wherein the catheter has an outer diameter range of less than 2 mm.
- 20 87. The method according to Claim 86, wherein the catheter has an inner diameter range of less than 2 mm.
88. The method according to Claim 80, wherein the needle is made from a
25 metallic, non-metallic, ceramic, and polymeric material and composites thereof.
89. The method of claim 80 wherein the beneficial agent is selected from a
30 drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-inflammatory agents, antiproliferative agents, antimitotic agents, angiogenic agents, anticoagulants, fibrinolytic agents,

growth factors, antibodies, ocular drugs, and metabolites, analogs, derivatives, and fragments thereof.

1/22




FIG. 1

2/22




FIG. 2

3/22




FIG. 3

4/22




FIG. 4

5/22




FIG. 5

6/22




FIG. 6

7/22




FIG. 7

8/22




FIG. 8

9/22




FIG. 9

10/22




FIG. 10

11/22




FIG. 11

12/22




FIG. 12

13/22

Bupivacaine plasma levels(ng/ml)




FIG. 13

14/22




FIG. 14

15/22




FIG. 15

16/22




FIG. 16

17/22




FIG. 17

18/22




FIG. 18

19/22




FIG. 19

20/22




FIG. 20

21/22




FIG. 21

22/22




FIG. 22

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 May 2003 (22.05.2003)

PCT

(10) International Publication Number
WO 03/041757 A3

(51) International Patent Classification⁷: A61K 9/00

(21) International Application Number: PCT/US02/36716

(22) International Filing Date:
14 November 2002 (14.11.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/336,307 14 November 2001 (14.11.2001) US
60/399,882 31 July 2002 (31.07.2002) US

(71) Applicant: ALZA CORPORATION [US/US]; 1900
Charleston Road, P.O. BOX 7210, Mountain View, CA
94039-7210 (US).

(72) Inventors: CHEN, Guohua; 399 Sunset Avenue, Sun-
nyvale, CA 94086 (US). HOUSTON, Paul, Ricky; 3889
Blackstone Court, Hayward, CA 94542 (US). KLEINER,

Lothar, Walther; 295 Los Altos Court, Los Altos, CA
94022 (US). WRIGHT, Jeremy, Corwin; 631 Cuesta
Drive, Los Altos, CA 94024-4135 (US).


(74) Agents: DATE, Vandana et al.; ALZA CORPORATION,
1900 Charleston Road, P.O. Box 7210,, Mountain View,
CA 94039-7210 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN,
YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: CATHETER INJECTABLE DEPOT COMPOSITIONS AND USES THEREOF



(57) Abstract: Catheter injectable depot compositions are provided that include a bioerodible, biocompatible polymer, a solvent having miscibility in water of less than or equal to 7 wt.% at 25°C, in an amount effective to plasticize the polymer and form a gel therewith, a thixotropic agent, and a beneficial agent. The solvent comprises an aromatic alcohol, an ester of an aromatic acid, an aromatic ketone, or mixtures thereof. The compositions are have substantially improved the shear thinning behavior and reduced injection force, rendering the compositions readily implanted beneath a patient's body surface by injection.

WO 03/041757 A3

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(88) Date of publication of the international search report:
12 September 2003

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 02/6716A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 A61K9/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, BIOSIS, MEDLINE, EMBASE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 93 24150 A (ZENECA LTD) 9 December 1993 (1993-12-09) page 26, paragraph 2 -page 29, paragraph 1 examples 16-20 claims	1-89
X	WO 95 13799 A (MEDISORB TECHNOLOGIES INTERNAT) 26 May 1995 (1995-05-26) example 1	1-13,34
X	WO 98 27963 A (ALZA CORP) 2 July 1998 (1998-07-02) example 2 & US 613 200 A cited in the application	1-89

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

23 June 2003

Date of mailing of the international search report

03/07/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 eno nl.
Fax: (+31-70) 340-3016

Authorized officer

Epskamp, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/36716

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 74650 A (ALZA CORP) 14 December 2000 (2000-12-14) example 1	1-89
P,X	WO 02 067991 A (GENENTECH INC) 6 September 2002 (2002-09-06) examples claims	1-89

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 02/36716

Box I Observations where certain claims were found unsearchable (Continuation of Item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

Although claims 68-89 are directed to a method of treatment of the human/animal body, the search has been carried out and based on the alleged effects of the composition.
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/36716

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9324150	A	09-12-1993	AT 407702 B	25-05-2001
			AT 901993 A	15-10-2000
			AU 682310 B2	02-10-1997
			AU 4084793 A	30-12-1993
			BE 1006143 A3	24-05-1994
			CA 2136751 A1	09-12-1993
			CH 688911 A5	29-05-1998
			CH 690491 A5	29-09-2000
			CZ 9402937 A3	15-03-1995
			DE 4392401 T0	24-07-1997
			DK 135394 A	28-11-1994
			ES 2107357 A1	16-11-1997
			FI 945553 A	25-01-1995
			FR 2691631 A1	03-12-1993
			WO 9324150 A1	09-12-1993
			GB 2282066 A , B	29-03-1995
			GR 1001550 B	29-04-1994
			HK 133097 A	24-10-1997
			HU 70177 A2	28-09-1995
			IE 930358 A1	01-12-1993
			IL 105710 A	19-03-2001
			IT M1931099 A1	28-12-1993
			JP 8501064 T	06-02-1996
			LU 88559 A1	05-04-1995
			MC 2330 A	31-05-1994
			NL 9320034 T	03-04-1995
			NO 944535 A	25-01-1995
			NZ 252268 A	20-12-1996
			RU 2152225 C1	10-07-2000
			SE 501970 C2	03-07-1995
			SE 9404115 A	28-11-1994
			SG 44645 A1	19-12-1997
			SK 143494 A3	11-07-1995
			US 6034175 A	07-03-2000
			US 5889110 A	30-03-1999
			US 2002198315 A1	26-12-2002
			ZA 9303358 A	15-09-1994
WO 9513799	A	26-05-1995	AT 212830 T	15-02-2002
			AU 684324 B2	11-12-1997
			AU 1101095 A	06-06-1995
			AU 697887 B2	22-10-1998
			AU 3683197 A	20-11-1997
			CA 2176716 A1	26-05-1995
			DE 69429820 D1	21-03-2002
			DE 69429820 T2	14-11-2002
			DK 729353 T3	27-05-2002
			EP 0729353 A1	04-09-1996
			EP 0998917 A1	10-05-2000
			ES 2172574 T3	01-10-2002
			JP 9505308 T	27-05-1997
			PT 729353 T	31-07-2002
			WO 9513799 A1	26-05-1995
			US 5654008 A	05-08-1997
			US 5650173 A	22-07-1997
WO 9827963	A	02-07-1998	AT 203157 T	15-08-2001
			AU 5609798 A	17-07-1998

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/36716

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
WO 9827963	A	AU 739469 B2	11-10-2001	
		AU 5615498 A	17-07-1998	
		DE 69705746 D1	23-08-2001	
		DE 69705746 T2	31-10-2001	
		DK 949905 T3	22-10-2001	
		EP 0949905 A2	20-10-1999	
		EP 0959873 A2	01-12-1999	
		ES 2158611 T3	01-09-2001	
		GR 3036599 T3	31-12-2001	
		HK 1020009 A1	02-11-2001	
		JP 2002512597 T	23-04-2002	
		JP 2001509146 T	10-07-2001	
		NZ 335851 A	23-02-2001	
		PT 949905 T	28-12-2001	
		WO 9827962 A2	02-07-1998	
		WO 9827963 A2	02-07-1998	
		US 2003044467 A1	06-03-2003	
		US 6468961 B1	22-10-2002	
		US 2002034532 A1	21-03-2002	
		US 6331311 B1	18-12-2001	
		US 6130200 A	10-10-2000	
WO 0074650	A	14-12-2000	AU 5462900 A	28-12-2000
			CA 2372994 A1	14-12-2000
			CZ 20014338 A3	13-03-2002
			EP 1183010 A2	06-03-2002
			HU 0201626 A2	28-12-2002
			JP 2003501375 T	14-01-2003
			NO 20015888 A	31-01-2002
			WO 0074650 A2	14-12-2000
WO 02067991	A	06-09-2002	US 2002173552 A1	21-11-2002
			WO 02067991 A1	06-09-2002